



Film Capacitors

EMI Suppression Capacitors (MKP)

Series/Type: B32923E/F ... B32928E/F

Date: May 2009

The following products presented in this data sheet are being withdrawn.

| Ordering Code | Substitute Product | Date of Withdrawal | Deadline Last Orders | Last Shipments |
|-----------------|--------------------|--------------------|----------------------|----------------|
| B32926E3335M000 | B32926C3335* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32926E3225M000 | B32926C3225* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32926E3225K000 | B32926C3225* | 2012-12-21 | 2013-03-31 | 2013-06-30 |

© EPCOS AG 2009. Reproduction, publication and dissemination of this publication, enclosures hereto and the information contained therein without EPCOS' prior express consent is prohibited.



| Ordering Code | Substitute Product | Date of Withdrawal | Deadline Last Orders | Last Shipments |
|-----------------|-----------------------------|--------------------|----------------------|----------------|
| B32926E3206M000 | B32928C3206 | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32926E3156M000 | B32926C3156M,B32926D3156 | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32926E3156K000 | B32926C3156M,B32926D3156 | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32926E3106M000 | B32926C3106* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32926E3106K000 | B32926C3106* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32924F3335K000 | B32924D3335K* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32924F3225K189 | B32924C3225* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32924F3225K000 | B32924C3225* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32924E3685M000 | B32926C3685* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32924E3475M000 | B32924C3475M* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32924E3565M000 | B32924C3565* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32924E3335M189 | B32924C3335M* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32924E3335M000 | B32924C3335M* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32924E3825M000 | B32926C3825* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32924E3225M189 | B32924C3225* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32924E3225M000 | B32924C3225* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32923E3335M000 | B32924C3335M*,B32924D3335K* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32923E3335K000 | B32924C3335M*,B32924D3335K* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32924F3685K000 | B32926C3685* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32924F3475K000 | B32924D3475K* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32923E3225M000 | B32923C3225* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32924F3565K000 | B32924C3565* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32928E3456M000 | | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32928E3406M000 | | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32928E3406K000 | | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32928E3306M000 | B32928C3306M* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32928E3306K000 | B32928C3306M* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32928E3256M000 | B32928C3256 | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32928E3256K000 | B32928C3256 | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32926F3206K000 | B32928C3206 | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32926E3685M000 | B32926C3685* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32926E3685K000 | B32926C3685* | 2012-12-21 | 2013-03-31 | 2013-06-30 |
| B32926E3475M000 | B32926C3475* | 2012-12-21 | 2013-03-31 | 2013-06-30 |

For further information please contact your nearest EPCOS sales office, which will also support you in selecting a suitable substitute. The addresses of our worldwide sales network are presented at www.epcos.com/sales.

Typical applications

- X2 class for interference suppression
- "Across the line" applications

Climatic

- Max. operating temperature: 110 °C
- Climatic category (IEC 60068-1): 40/110/56

Construction

- Dielectric: polypropylene (MKP)
- Plastic case (UL 94 V-0)
- Epoxy resin sealing (UL 94 V-0)

Features

- Capacitance value up to 45 µF
- Very small dimensions
- Good self-healing properties
- High voltage capability

Terminals

- Parallel wire leads, lead-free tinned
- Standard lead lengths: 6 – 1 mm
- Special lead lengths available on request

Marking

Manufacturer's logo, lot number, date code, rated capacitance (coded), capacitance tolerance (code letter), rated AC voltage (IEC), series number, sub-class (X2), dielectric code (MKP), climatic category, passive flammability category, approvals.

Delivery mode


Bulk (untaped)

Reel


For taping details, refer to chapter "Taping and packing"

Dimensional drawings

Drawing 1



Drawing 2




Dimensions in mm

| Lead spacing $e \pm 0.4$ | Lead diameter d_1 | Type | Drawing |
|-----------------------------|------------------------|-----------|---------|
| 22.5 | 0.8 | B32923E | 1 |
| 27.5 | 0.8 | B32924E/F | 1 |
| 37.5 | 1.0 | B32926E/F | 1 |
| 52.5 | 1.2 | B32928E | 2 |




Marking example



KMK1258-5




Approvals

| Approval marks | Standards | Certificate |
|---|----------------|-------------|
|  | IEC 60384-14 | 40021331 |
|  | UL 1283 | E301966 |
|  ¹⁾ | CSA C22.2 No.8 | E301966 |

1) approved by UL

Overview of available types

| Lead spacing | 22.5 mm | 27.5 mm | 37.5 mm | 52.5 mm |
|---------------------|---------|-----------|-----------|---------|
| Type | B32923E | B32924E/F | B32926E/F | B32928E |
| C _R (μF) | | | | |
| 2.2 | | | | |
| 3.3 | | | | |
| 4.7 | | | | |
| 5.6 | | | | |
| 6.8 | | | | |
| 8.2 | | | | |
| 10 | | | | |
| 15 | | | | |
| 20 | | | | |
| 25 | | | | |
| 30 | | | | |
| 40 | | | | |
| 45 | | | | |


B32923E/F ... B32928E/F
Efficient filtering – X2 / 305 V AC

Ordering codes and packing units

| Lead spacing | C _R | Max. dimensions w × h × l mm | Ordering code (composition see below) | Reel pcs./MOQ | Untaped pcs./MOQ |
|--------------|----------------|------------------------------------|---|------------------|---------------------|
| mm | μF | mm | | | |
| 22.5 | 2.2 | 12.0 × 22.0 × 26.5 | B32923E3225M*** ◆ | — | 1800 |
| | 3.3 | 14.5 × 29.5 × 26.5 | B32923E3335+*** | — | 1040 |
| 27.5 | 2.2 | 11.0 × 21.0 × 31.5 | B32924E3225M*** | 1400 | 2352 |
| | 2.2 | 12.5 × 21.5 × 31.5 | B32924F3225K*** | 1200 | 2100 |
| | 3.3 | 14.0 × 24.5 × 31.5 | B32924E3335M*** ◆ | 1000 | 1848 |
| | 3.3 | 15.0 × 24.0 × 31.5 | B32924F3335K*** | — | 1680 |
| | 4.7 | 16.0 × 32.0 × 31.5 | B32924F3475K*** | — | 1064 |
| | 4.7 | 18.0 × 27.5 × 31.5 | B32924E3475M*** ◆ | — | 1428 |
| | 5.6 | 18.0 × 33.0 × 31.5 | B32924F3565K*** | — | 952 |
| | 5.6 | 19.0 × 30.0 × 31.5 | B32924E3565M*** | — | 896 |
| | 6.8 | 21.0 × 31.0 × 31.5 | B32924E3685M*** ◆ | — | 784 |
| | 6.8 | 22.0 × 36.5 × 31.5 | B32924F3685K*** | — | 784 |
| 37.5 | 8.2 | 22.0 × 36.5 × 31.5 | B32924E3825M*** ◆ | — | 784 |
| | 2.2 | 12.0 × 22.0 × 42.0 | B32926E3225+*** | — | 1620 |
| | 3.3 | 12.0 × 22.0 × 42.0 | B32926E3335M*** | — | 1620 |
| | 4.7 | 14.0 × 25.0 × 42.0 | B32926E3475M*** | — | 1380 |
| | 6.8 | 18.0 × 32.5 × 42.0 | B32926E3685+*** | — | 720 |
| | 10 | 20.0 × 39.5 × 42.0 | B32926E3106+*** ◆ | — | 640 |
| | 15 | 28.0 × 37.0 × 42.0 | B32926E3156+*** ◆ | — | 440 |
| | 20 | 28.0 × 42.5 × 42.0 | B32926E3206M*** ◆ | — | 440 |
| 52.5 | 20 | 30.0 × 45.0 × 42.0 | B32926F3206K*** | — | 200 |
| | 25 | 30.0 × 45.0 × 57.5 | B32928E3256+*** ◆ | — | 280 |
| | 30 | 30.0 × 45.0 × 57.5 | B32928E3306+*** ◆ | — | 280 |
| | 40 | 35.0 × 50.0 × 57.5 | B32928E3406+*** ◆ | — | 108 |
| | 45 | 35.0 × 50.0 × 57.5 | B32928E3456M*** ◆ | — | 108 |

◆ Preferred type

MOQ = Minimum Order Quantity, consisting of 4 packing units.

Further intermediate capacitance values on request.

Composition of ordering code

+ = Capacitance tolerance code:


M = ±20%

K = ±10%

*** = Packaging code:

189 = Reel

000 = Untaped (lead length 6 – 1 mm)



Technical data

| | |
|--|--------------------------------|
| Maximum continuous DC voltage V_{DC} | 500 V |
| Maximum continuous AC voltage V_{AC} | 310 V (50/60 Hz) |
| Rated AC voltage (IEC 60384-14) | 305 V (50/60 Hz) |
| Max. operating temperature $T_{op,max}$ | +110 °C |
| DC test voltage | 2121 V, 2 s |
| Dissipation factor $\tan \delta$ (in 10^{-3}) at 20 °C (upper limit values) | at 1 kHz: 2 |
| Insulation resistance R_{ins} or time constant $\tau = C_R \cdot R_{ins}$ at 100 V DC, 20 °C, rel. humidity $\leq 65\%$ and for 60 s (minimum as-delivered values) | 30 000 s |
| Passive flammability category to IEC 40 (CO) 752 | B |
| Capacitance tolerances (measured at 1 kHz) | $\pm 10\%$ (K), $\pm 20\%$ (M) |

Pulse handling capability

"dV/dt" represents the maximum permissible voltage change per unit of time for non-sinusoidal voltages, expressed in V/ μ s.


" k_0 " represents the maximum permissible pulse characteristic of the waveform applied to the capacitor, expressed in V²/ μ s.

Note:

The values of dV/dt and k_0 provided below must not be exceeded in order to avoid damaging the capacitor.

dV/dt and k_0 values


| | | | | |
|-----------------------------------|---------|---------|---------|---------|
| Lead spacing | 22.5 mm | 27.5 mm | 37.5 mm | 52.5 mm |
| dV/dt in V/ μ s | 140 | 100 | 70 | 40 |
| k_0 in V ² / μ s | 120 400 | 86 000 | 60 200 | 34 400 |




B32923E/F ... B32928E/F

Efficient filtering – X2 / 305 V AC

Impedance Z versus frequency f (typical values)





Mounting guidelines

1 Soldering

1.1 Solderability of leads

The solderability of terminal leads is tested to IEC 60068-2-20, test Ta, method 1.

Before a solderability test is carried out, terminals are subjected to accelerated ageing (to IEC 60068-2-2, test Ba: 4 h exposure to dry heat at 155 °C). Since the ageing temperature is far higher than the upper category temperature of the capacitors, the terminal wires should be cut off from the capacitor before the ageing procedure to prevent the solderability being impaired by the products of any capacitor decomposition that might occur.


| | |
|-------------------------|---|
| Solder bath temperature | 235 ±5 °C |
| Soldering time | 2.0 ±0.5 s |
| Immersion depth | 2.0 +0/–0.5 mm from capacitor body or seating plane |
| Evaluation criteria: | |
| Visual inspection | Wetting of wire surface by new solder ≥90%, free-flowing solder |

1.2 Resistance to soldering heat

Resistance to soldering heat is tested to IEC 60068-2-20, test Tb, method 1A.


Conditions:

| Series | Solder bath temperature | Soldering time |
|--|-------------------------|---|
| MKT boxed (except 2.5 × 6.5 × 7.2 mm) coated uncoated (lead spacing > 10 mm) | 260 ±5 °C | 10 ±1 s |
| MFP | | |
| MKP (lead spacing > 7.5 mm) | | |
| MKT boxed (case 2.5 × 6.5 × 7.2 mm) | | 5 ±1 s |
| MKP (lead spacing ≤ 7.5 mm) | | < 4 s |
| MKT uncoated (lead spacing ≤ 10 mm) insulated (B32559) | | recommended soldering profile for MKT uncoated (lead spacing ≤ 10 mm) and insulated (B32559) |



B32923E/F ... B32928E/F

Efficient filtering – X2 / 305 V AC



| | |
|----------------------|---|
| Immersion depth | 2.0 +0/–0.5 mm from capacitor body or seating plane |
| Shield | Heat-absorbing board, (1.5 ±0.5) mm thick, between capacitor body and liquid solder |
| Evaluation criteria: | |
| Visual inspection | No visible damage |
| $\Delta C/C_0$ | 2% for MKT/MKP/MFP 5% for EMI suppression capacitors |
| $\tan \delta$ | As specified in sectional specification |

1.3 General notes on soldering

Permissible heat exposure loads on film capacitors are primarily characterized by the upper category temperature T_{\max} . Long exposure to temperatures above this type-related temperature limit can lead to changes in the plastic dielectric and thus change irreversibly a capacitor's electrical characteristics. For short exposures (as in practical soldering processes) the heat load (and thus the possible effects on a capacitor) will also depend on other factors like:

- Pre-heating temperature and time
- Forced cooling immediately after soldering
- Terminal characteristics:
diameter, length, thermal resistance, special configurations (e.g. crimping)
- Height of capacitor above solder bath
- Shadowing by neighboring components
- Additional heating due to heat dissipation by neighboring components
- Use of solder-resist coatings

The overheating associated with some of these factors can usually be reduced by suitable countermeasures. For example, if a pre-heating step cannot be avoided, an additional or reinforced cooling process may possibly have to be included.


EPCOS recommends the following conditions:

- Pre-heating with a maximum temperature of 110 °C
- Temperature inside the capacitor should not exceed the following limits:
 - MKP/MFP 110 °C
 - MKT 160 °C
- When SMD components are used together with leaded ones, the leaded film capacitors should not pass into the SMD adhesive curing oven. The leaded components should be assembled after the SMD curing step.
- Leaded film capacitors are not suitable for reflow soldering.

Uncoated capacitors

For uncoated MKT capacitors with lead spacings ≤ 10 mm (B32560/B32561) the following measures are recommended:

- pre-heating to not more than 110 °C in the preheater phase
- rapid cooling after soldering



B32923E/F ... B32928E/F

Efficient filtering – X2 / 305 V AC

2 Cleaning

To determine whether the following solvents, often used to remove flux residues and other substances, are suitable for the capacitors described, refer to the table below:

| Type | Ethanol, isopropanol, n-propanol | n-propanol-water mixtures, water with surface tension-reducing tensides (neutral) | Solvent from table A (see next page) | Solvent from table B (see next page) |
|------------------------------|----------------------------------|---|--------------------------------------|--------------------------------------|
| MKT (uncoated) | Suitable | Unsuitable | In part suitable | Unsuitable |
| MKT, MKP, MFP (coated/boxed) | | Suitable | Suitable | |

Even when suitable solvents are used, a reversible change of the electrical characteristics may occur in uncoated capacitors immediately after they are washed. Thus it is always recommended to dry the components (e.g. 4 h at 70 °C) before they are subjected to subsequent electrical testing.

Table A


Manufacturers' designations for trifluoro-trichloro-ethane-based cleaning solvents (selection)

| Trifluoro-trichloro-ethane | Mixtures of trifluoro-trichloro-ethane with ethanol and isopropanol | Manufacturer |
|----------------------------|---|--------------|
| Freon TF | Freon TE 35; Freon TP 35; Freon TES | Du Pont |
| Frigen 113 TR | Frigen 113 TR-E; Frigen 113 TR-P; Frigen TR-E 35 | Hoechst |
| Arklone P | Arklone A; Arklone L; Arklone K | ICI |
| Kaltron 113 MDR | Kaltron 113 MDA; Kaltron 113 MDI; Kaltron 113 MDI 35 | Kali-Chemie |
| Flugene 113 | Flugene 113 E; Flugene 113 IPA | Rhone-Progil |

Table B (worldwide banned substances)

Manufacturers' designations for unsuitable cleaning solvents (selection)

| Mixtures of chlorinated hydrocarbons and ketones with fluorated hydrocarbons | Manufacturer |
|--|--------------|
| Freon TMC; Freon TA; Freon TC | Du Pont |
| Arklone E | ICI |
| Kaltron 113 MDD; Kaltron 113 MDK | Kali-Chemie |
| Flugene 113 CM | Rhone-Progil |




3 Embedding of capacitors in finished assemblies

In many applications, finished circuit assemblies are embedded in plastic resins. In this case, both chemical and thermal influences of the embedding ("potting") and curing processes must be taken into account.

Our experience has shown that the following potting materials can be recommended: non-flexible epoxy resins with acid-anhydride hardeners; chemically inert, non-conducting fillers; maximum curing temperature of 100 °C.

Caution:

Consult us first if you wish to embed uncoated types!




Cautions and warnings


- Do not exceed the upper category temperature (UCT).
- Do not apply any mechanical stress to the capacitor terminals.
- Avoid any compressive, tensile or flexural stress.
- Do not move the capacitor after it has been soldered to the PC board.
- Do not pick up the PC board by the soldered capacitor.
- Do not place the capacitor on a PC board whose PTH hole spacing differs from the specified lead spacing.
- Do not exceed the specified time or temperature limits during soldering.
- Avoid external energy inputs, such as fire or electricity.
- Avoid overload of the capacitors.

The table below summarizes the safety instructions that must always be observed. A detailed description can be found in the relevant sections of the chapters "General technical information" and "Mounting guidelines".

| Topic | Safety information | Reference chapter "General technical information" |
|-------------------------|---|---|
| Storage conditions | Make sure that capacitors are stored within the specified range of time, temperature and humidity conditions. | 4.5 "Storage conditions" |
| Flammability | Avoid external energy, such as fire or electricity (passive flammability), avoid overload of the capacitors (active flammability) and consider the flammability of materials. | 5.3 "Flammability" |
| Resistance to vibration | Do not exceed the tested ability to withstand vibration. The capacitors are tested to IEC 60068-2-6. EPCOS offers film capacitors specially designed for operation under more severe vibration regimes such as those found in automotive applications. Consult our catalog "Film Capacitors for Automotive Electronics". | 5.2 "Resistance to vibration" |




| Topic | Safety information | Reference chapter "Mounting guidelines" |
|--|---|--|
| Soldering | Do not exceed the specified time or temperature limits during soldering. | 1 "Soldering" |
| Cleaning | Use only suitable solvents for cleaning capacitors. | 2 "Cleaning" |
| Embedding of capacitors in finished assemblies | When embedding finished circuit assemblies in plastic resins, chemical and thermal influences must be taken into account. Caution: Consult us first, if you also wish to embed other uncoated component types! | 3 "Embedding of capacitors in finished assemblies" |




Symbols and terms

| Symbol | English | German |
|----------------------|---|---|
| α | Heat transfer coefficient | Wärmeübergangszahl |
| α_C | Temperature coefficient of capacitance | Temperaturkoeffizient der Kapazität |
| A | Capacitor surface area | Kondensatoroberfläche |
| β_C | Humidity coefficient of capacitance | Feuchtekoeffizient der Kapazität |
| C | Capacitance | Kapazität |
| C_R | Rated capacitance | Nennkapazität |
| ΔC | Absolute capacitance change | Absolute Kapazitätsänderung |
| $\Delta C/C$ | Relative capacitance change (relative deviation of actual value) | Relative Kapazitätsänderung (relative Abweichung vom Ist-Wert) |
| $\Delta C/C_R$ | Capacitance tolerance (relative deviation from rated capacitance) | Kapazitätstoleranz (relative Abweichung vom Nennwert) |
| dt | Time differential | Differentielle Zeit |
| Δt | Time interval | Zeitintervall |
| ΔT | Absolute temperature change (self-heating) | Absolute Temperaturänderung (Selbsterwärmung) |
| $\Delta \tan \delta$ | Absolute change of dissipation factor | Absolute Änderung des Verlustfaktors |
| ΔV | Absolute voltage change | Absolute Spannungsänderung |
| dV/dt | Time differential of voltage function (rate of voltage rise) | Differentielle Spannungsänderung (Spannungsflankensteilheit) |
| $\Delta V/\Delta t$ | Voltage change per time interval | Spannungsänderung pro Zeitintervall |
| E | Activation energy for diffusion | Aktivierungsenergie zur Diffusion |
| ESL | Self-inductance | Eigeninduktivität |
| ESR | Equivalent series resistance | Ersatz-Serienwiderstand |
| f | Frequency | Frequenz |
| f_1 | Frequency limit for reducing permissible AC voltage due to thermal limits | Grenzfrequenz für thermisch bedingte Reduzierung der zulässigen Wechselspannung |
| f_2 | Frequency limit for reducing permissible AC voltage due to current limit | Grenzfrequenz für strombedingte Reduzierung der zulässigen Wechselspannung |
| f_r | Resonant frequency | Resonanzfrequenz |
| F_D | Thermal acceleration factor for diffusion | Therm. Beschleunigungsfaktor zur Diffusion |
| F_T | Derating factor | Deratingfaktor |
| i | Current (peak) | Stromspitze |
| I_C | Category current (max. continuous current) | Kategoriestrom (max. Dauerstrom) |



| Symbol | English | German |
|------------------|--|---|
| I_{RMS} | (Sinusoidal) alternating current, root-mean-square value | (Sinusförmiger) Wechselstrom |
| i_z | Capacitance drift | Inkonstanz der Kapazität |
| k_0 | Pulse characteristic | Impulskennwert |
| L_S | Series inductance | Serieninduktivität |
| λ | Failure rate | Ausfallrate |
| λ_0 | Constant failure rate during useful service life | Konstante Ausfallrate in der Nutzungsphase |
| λ_{test} | Failure rate, determined by tests | Experimentell ermittelte Ausfallrate |
| P_{diss} | Dissipated power | Abgegebene Verlustleistung |
| P_{gen} | Generated power | Erzeugte Verlustleistung |
| Q | Heat energy | Wärmeenergie |
| ρ | Density of water vapor in air | Dichte von Wasserdampf in Luft |
| R | Universal molar constant for gases | Allg. Molarkonstante für Gas |
| R | Ohmic resistance of discharge circuit | Ohmscher Widerstand des Entladekreises |
| R_i | Internal resistance | Innenwiderstand |
| R_{ins} | Insulation resistance | Isolationswiderstand |
| R_P | Parallel resistance | Parallelwiderstand |
| R_S | Series resistance | Serienwiderstand |
| S | severity (humidity test) | Schärfegrad (Feuchtest) |
| t | Time | Zeit |
| T | Temperature | Temperatur |
| τ | Time constant | Zeitkonstante |
| $\tan \delta$ | Dissipation factor | Verlustfaktor |
| $\tan \delta_D$ | Dielectric component of dissipation factor | Dielektrischer Anteil des Verlustfaktors |
| $\tan \delta_P$ | Parallel component of dissipation factor | Parallelanteil des Verlustfaktors |
| $\tan \delta_S$ | Series component of dissipation factor | Serienanteil des Verlustfaktors |
| T_A | Ambient temperature | Umgebungstemperatur |
| T_{max} | Upper category temperature | Obere Kategorietemperatur |
| T_{min} | Lower category temperature | Untere Kategorietemperatur |
| t_{OL} | Operating life at operating temperature and voltage | Betriebszeit bei Betriebstemperatur und -spannung |
| T_{op} | Operating temperature | Betriebstemperatur |
| T_R | Rated temperature | Nenntemperatur |
| T_{ref} | Reference temperature | Referenztemperatur |
| t_{SL} | Reference service life | Referenz-Lebensdauer |
| V_{AC} | AC voltage | Wechselspannung |



B32923E/F ... B32928E/F

Efficient filtering – X2 / 305 V AC

| Symbol | English | German |
|-------------|---|---|
| V_C | Category voltage | Kategoriespannung |
| $V_{C,RMS}$ | Category AC voltage | (Sinusförmige) Kategorie-Wechselspannung |
| V_{CD} | Corona-discharge onset voltage | Teilentlade-Einsatzspannung |
| V_{ch} | Charging voltage | Ladespannung |
| V_{DC} | DC voltage | Gleichspannung |
| V_{FB} | Fly-back capacitor voltage | Spannung (Flyback) |
| V_i | Input voltage | Eingangsspannung |
| V_o | Output voltage | Ausgangssspannung |
| V_{op} | Operating voltage | Betriebsspannung |
| V_p | Peak pulse voltage | Impuls-Spitzenspannung |
| V_{pp} | Peak-to-peak voltage Impedance | Spannungshub |
| V_R | Rated voltage | Nennspannung |
| \hat{V}_R | Amplitude of rated AC voltage | Amplitude der Nenn-Wechselspannung |
| V_{RMS} | (Sinusoidal) alternating voltage, root-mean-square value | (Sinusförmige) Wechselspannung |
| V_{SC} | S-correction voltage | Spannung bei Anwendung "S-correction" |
| V_{sn} | Snubber capacitor voltage | Spannung bei Anwendung "Beschaltung" |
| Z | Impedance | Scheinwiderstand |
| e | Lead spacing | Rastermaß |

Important notes

The following applies to all products named in this publication:

1. Some parts of this publication contain **statements about the suitability of our products for certain areas of application**. These statements are based on our knowledge of typical requirements that are often placed on our products in the areas of application concerned. We nevertheless expressly point out **that such statements cannot be regarded as binding statements about the suitability of our products for a particular customer application**. As a rule, EPCOS is either unfamiliar with individual customer applications or less familiar with them than the customers themselves. For these reasons, it is always ultimately incumbent on the customer to check and decide whether an EPCOS product with the properties described in the product specification is suitable for use in a particular customer application.
2. We also point out that **in individual cases, a malfunction of electronic components or failure before the end of their usual service life cannot be completely ruled out in the current state of the art, even if they are operated as specified**. In customer applications requiring a very high level of operational safety and especially in customer applications in which the malfunction or failure of an electronic component could endanger human life or health (e.g. in accident prevention or lifesaving systems), it must therefore be ensured by means of suitable design of the customer application or other action taken by the customer (e.g. installation of protective circuitry or redundancy) that no injury or damage is sustained by third parties in the event of malfunction or failure of an electronic component.
3. **The warnings, cautions and product-specific notes must be observed.**
4. In order to satisfy certain technical requirements, **some of the products described in this publication may contain substances subject to restrictions in certain jurisdictions (e.g. because they are classed as hazardous)**. Useful information on this will be found in our Material Data Sheets on the Internet (www.epcos.com/material). Should you have any more detailed questions, please contact our sales offices.
5. We constantly strive to improve our products. Consequently, **the products described in this publication may change from time to time**. The same is true of the corresponding product specifications. Please check therefore to what extent product descriptions and specifications contained in this publication are still applicable before or when you place an order. We also **reserve the right to discontinue production and delivery of products**. Consequently, we cannot guarantee that all products named in this publication will always be available. The aforementioned does not apply in the case of individual agreements deviating from the foregoing for customer-specific products.
6. Unless otherwise agreed in individual contracts, **all orders are subject to the current version of the "General Terms of Delivery for Products and Services in the Electrical Industry" published by the German Electrical and Electronics Industry Association (ZVEI)**.
7. The trade names EPCOS, BAOKE, Alu-X, CeraDiode, CSMP, CSSP, CTVS, DSSP, MiniBlue, MiniCell, MKK, MLSC, MotorCap, PCC, PhaseCap, PhaseCube, PhaseMod, PhiCap, SIFERRIT, SIFI, SIKOREL, SilverCap, SIMDAD, SIMID, SineFormer, SIOV, SIP5D, SIP5K, ThermoFuse, WindCap are **trademarks registered or pending** in Europe and in other countries. Further information will be found on the Internet at www.epcos.com/trademarks.

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

EPCOS:

[B32928E3256M000](#)