X8R/X8L Dielectric

General Specifications



AVX has developed a range of multilayer ceramic capacitors designed for use in applications up to 150°C. These capacitors are manufactured with an X8R and an X8L dielectric material. X8R material has capacitance variation of \pm 15% between -55°C and +150°C. The X8L material has capacitance variation of \pm 15% between -55°C to 125°C and +15/-40% from +125°C to +150°C.

The need for X8R and X8L performance has been driven by customer requirements for parts that operate at elevated temperatures. They provide a highly reliable capacitor with low loss and stable capacitance over temperature.

They are ideal for automotive under the hood sensors, and various industrial applications. Typical industrial application would be drilling monitoring system. They can also be used as bulk capacitors for high temperature camera modules.

Both X8R and X8L dielectric capacitors are automotive AEC-Q200 qualified. Optional termination systems, tin, FLEXITERM® and conductive epoxy for hybrid applications are available. Providing this series with our FLEXITERM® termination system provides further advantage to customers by way of enhanced resistance to both, temperature cycling and mechanical damage.

PART NUMBER (see page 2 for complete part number explanation)



NOTE: Contact factory for availability of Termination and Tolerance Options for Specific Part Numbers.

			X	BR											X8L						
SIZE		0	0603		0805		1206		SIZE			0603			0805			1206			
Soldering		Reflow/Wave		Reflow/Wave		Ret	Reflow/Wave		Soldering		Reflow/Wave		Reflow/Wave			Reflow/Wave					
	WVDC	25V	50V	25V	50V	25V	50V			WVI	DC	25V	50V	100V	25V	50V	100V	16V	25V	50V	100V
331	Cap 330	G	G	J	J				331	Cap	330		G	G		J	J				
471	(pF) 470	G	G	J	J				471	(pF)	470		G	G		J	J				
681	680	G	G	J	J				681		680		G	G		J	J				
102	1000	G	G	J	J	J	J		102		1000		G	G		J	J				
152	1500	G	G	J	J	J	J		152		1500		G	G		J	J			J	J
222	2200	G	G	J	J	J	J		222		2200		G	G		J	J			J	J
332	3300	G	G	J	J	J	J		332		3300		G	G		J	J			J	J
472	4700	G	G	J	J	J	J		472		4700		G	G		J	J			J	J
682	6800	G	G	J	J	J	J		682		6800		G	G		J	J			J	J
103	Cap 0.01	G	G	J	J	J	J		103		0.01		G	G		J	J			J	J
153	(µF) 0.015	G	G	J	J	J	J		153	(µF) (0.015	G	G		J	J	J			J	J
223	0.022	G	G	J	J	J	J		223	().022	G	G		J	J	J			J	J
333	0.033	G	G	J	J	J	J		333	(0.033	G	G		J	J	N			J	J
473	0.047	G	G	J	J	J	J		473	().047	G	G		J	J	N			J	J
683	0.068	G		N	N	M	M		683	().068	G	G		J	J				J	J
104	0.1			N	N	M	M		104		0.1	G	G		J	J				J	M
154	0.15			N	N	M	M		154		0.15				J	N		J	J	J	Q
224	0.22			N		M	M		224		0.22				N	N		J	J	J	Q
334	0.33	1				M	M		334		0.33				N			J	M	P	Q
474	0.47	1				M			474		0.47				N			M	M	P	
684	0.68								684		0.68							М			
105	1								105		1							М			
	WVDC	25V	50V	25V	50V	25V	50\	,		WVI	DC	25V	50V	100V	25V	50V	100V	16V	25V	50V	100V
	SIZE		0603		0805		1206		SIZE			0603		0805				1206			
Lett	er A				G	J	К	1	M	N		P	Q		Х	Y		Z] = AE	C-Q200
Ma	x. 0.30	3 0.5			0.90	0.94	1.02	1.	.27	1.40	1	.52	1.78	2	2.29	2.54	l I	2.79		Qu	alified

(0.055)

(0.040) (0.050)

(0.060) (0.070)

EMBOSSED

(0.090) (0.100)

(0.110)

RoHS COMPLIANT

Thickness

(0.013)

(0.022)

(0.028)

PAPER

(0.035)

(0.037)

X8R/X8L Dielectric

General Specifications

APPLICATIONS FOR X8R AND X8L CAPACITORS

- All market sectors with a 150°C requirement
- Automotive on engine applications
- Oil exploration applications
- Hybrid automotive applications
 - Battery control
- Inverter / converter circuits
- Motor control applications
- Water pump
- Hybrid commercial applications
 - Emergency circuits
 - Sensors
 - Temperature regulation





ADVANTAGES OF X8R AND X8L MLC CAPACITORS

- Both ranges are qualified to the highest automotive AEC-Q200 standards
- Excellent reliability compared to other capacitor technologies
- RoHS compliant
- Low ESR / ESL compared to other technologies
- Tin solder finish
- FLEXITERM[®] available
- Epoxy termination for hybrid available
- 100V range available

ENGINEERING TOOLS FOR HIGH VOLTAGE MLC CAPACITORS

- Samples
- Technical Articles
- Application Engineering
- Application Support



X8R/X8L Dielectric

Specifications and Test Methods

Parame	ter/Test	X8R/X8L Specification Limits	Measuring Conditions					
	perature Range	-55°C to +150°C	Temperature Cycle Chamber					
Capac		Within specified tolerance	Freq.: 1.0 kHz ± 10% Voltage: 1.0Vrms ± .2V					
Dissipatio	on Factor	$\leq 2.5\%$ for $\geq 50V$ DC rating						
Dissipatio		\leq 3.5% for 25V DC and 16V DC rating						
Insulation I	Posistanco	100,000MΩ or 1000MΩ - μF,	Charge device with rated voltage for 120 ± 5 secs @ room temp/humidity Charge device with 300% of rated voltage for 1-5 seconds, w/charge and discharge current limited to 50 mA (max) Note: Charge device with 150% of rated voltage for 500V devices.					
Insulation	nesistance	whichever is less						
Dielectric	Strength	No breakdown or visual defects						
	Appearance	No defects	Deflectio					
	Capacitance		Test Time: 30 seconds					
Resistance to	Variation	≤ ±12%						
Flexure	Dissipation							
Stresses	Factor	Meets Initial Values (As Above)						
	Insulation							
	Resistance	≥ Initial Value x 0.3	90 mm					
Solder	rability	≥ 95% of each terminal should be covered with fresh solder	Dip device in eutectic solder at $230 \pm 5^{\circ}$ C for 5.0 \pm 0.5 seconds					
	Appearance	No defects, <25% leaching of either end terminal	101 010 2 01	0.00001100				
	Capacitance		 Dip device in eutectic solder at 260°C for 60 seconds. Store at room temperature for 24 ± 2 hours before measuring electrical properties. 					
	Variation	$\leq \pm 7.5\%$						
Desistance to	Dissipation							
Resistance to Solder Heat	Factor	Meets Initial Values (As Above)						
Solder Heat	Insulation	Meets Initial Values (As Above)						
	Resistance	IVIEELS IIIILIAI VAIUES (AS ADOVE)						
	Dielectric	Meets Initial Values (As Above)						
	Strength	, , ,	01 4 5500 00					
	Appearance	No visual defects	Step 1: -55°C ± 2°	30 ± 3 minutes				
	Capacitance Variation	$\leq \pm 7.5\%$	Step 2: Room Temp	≤ 3 minutes				
	Dissipation							
Thermal	Factor	Meets Initial Values (As Above)	Step 3: +125°C ± 2°	30 ± 3 minutes				
Shock	Insulation							
	Resistance	Meets Initial Values (As Above)	Step 4: Room Temp	≤ 3 minutes				
	Dielectric		Repeat for 5 cycles and measure after					
	Strength	Meets Initial Values (As Above)	24 ± 2 hours at room temperature					
	Appearance	No visual defects						
	Capacitance	≤ ±12.5%	Charge device with 1.5 rated voltage (≤ 10V) in test chamber set at 150°C ± 2°C for 1000 hours (+48, -0)					
	Variation							
	Dissipation	\leq Initial Value x 2.0 (See Above)						
Load Life	Factor			and a second of the				
	Insulation	\geq Initial Value x 0.3 (See Above)	Remove from test ch					
	Resistance		at room temperature for 24 ± 2 hours before measuring.					
	Dielectric	Meets Initial Values (As Above)						
	Strength	No visual defects						
	Appearance Capacitance		Store in a test chamb					
	Variation	≤ ±12.5%	$85\% \pm 5\%$ relative humidity for 1000 hours					
Load	Dissipation		(+48, -0) with rated voltage applied.					
Humidity	Factor	\leq Initial Value x 2.0 (See Above)	Remove from chamber and stabilize at room temperature and humidity for 24 ± 2 hours before measuring.					
	Insulation							
	Resistance	\geq Initial Value x 0.3 (See Above)						
	-		$1 \qquad 24 + 2$ hours be	tore measuring				
	Dielectric	Meets Initial Values (As Above)		iere medeannig.				