

Ferrite Components for the Electronics Industry


Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

Fair-Rite Product's Catalog Part Data Sheet, 2944777721 Printed: 2013-07-03









Part Number: 2944777721

Frequency Range: Broadband Frequencies 1-200 MHz (44 material)

Description: 44 WOUND BEAD

Application: Suppression Components

Where Used: Board Component

Part Type: Wound Beads


Mechanical Specifications

Weight: 3.900 (g)

Part Type Information

Six and eleven hole beads, in two NiZn materials, are available both as beads (product class 26) and wound with tinned copper wire in several winding configurations (product class 29).

- -Parts with a '1' as the last digit of the part number are supplied bulk packed. Wound beads with part numbers 29--666631 and 29--666651 can be supplied radially taped and reeled per IEC 60286-1 and EIA 468-B standards. For these taped and reeled wound beads the last digit of the part number is a '4'. Taped and reeled wound beads are supplied 500 pieces on a 13" reel.
- -Wire used for winding is oxygen free high conductivity copper with 100% matte tin plating over a nickel undercoating.
- -Beads are controlled for impedance limits only. Minimum impedance values are specified for the + marked frequencies. The minimum impedance is typically the listed impedance less 20%. The 44 material beads and wound beads are tested on the 4193A Vector Impedance Meter. The 61 material parts on the 4291A RF Impedance Analyzer.
- -Recommended storage temperature and operating temperature is -55°C to 125°C
- -For any wound bead requirement not listed in here, please contact our customer service group for availability and pricing.
- -Explanation of Part Numbers: Digits 1&2 = product class, 3&4 = material grade and last digit 1 = bulk packed, 4 = taped and reeled.



Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

Fair-Rite Product's Catalog Part Data Sheet, 2944777721 Printed: 2013-07-03







Mechanical Specifications

Dim	mm	mm	nominal	inch
		tol	inch	misc.
Α	10.00	±0.25	0.394	-
В	0.90	+0.15	0.038	-
С	10.00	±0.25	0.394	-
D	7.50	Ref	0.295	Ref
E	1	1	-	-
F	1	1	-	-
G	-	1	-	-
Н	-		-	-
J	-		-	-
K	-	-	-	-

Electrical Specifications

Typical Impedance (Ω)			
1 MHz	45		
10 MHz+	375		
50 MHz+	905		
100 MHz+	500		
200 MHz	400		

Electrical Properties	

Land Patterns

V	W ref	Х	Υ	Z
-	-			

Winding Information

Turns	Wire		1st Wire		2nd Wire		
Tested	Size		Length		Length		
2 x 2½	0.65 2	22 AWG	38.0 ±3.0	1.500	28.0 ±3.0	1.1	02

Reel Information

Tape Width	Pitch	Parts 7 "	Parts 13 "	Parts 14 "
mm	mm	Reel	Reel	Reel
-	-	-	-	-

Package Size

Pkg Size
-
(-)

Connector Plate

# Holes	# Rows		
-	-		

Legend

+ Test frequency

Preferred parts, the suggested choice for new designs, have shorter lead times and are more readily available.

The column H(Oe) gives for each bead the calculated dc bias field in oersted for 1 turn and 1 ampere direct current. The actual dc H field in the application is this value of H times the actual NI (ampere-turn) product. For the effect of the dc bias on the impedance of the bead material, see figures 18-23 in the application note How to choose Ferrite Components for EMI Suppression.

A ½ turn is defined as a single pass through a hole.

∠I/A - Core Constant

A_e: Effective Cross-Sectional Area

 A_{I} - Inductance Factor $\left(\frac{L}{N^{2}}\right)$

I e: Effective Path Length

Ve: Effective Core Volume

NI - Value of dc Ampere-turns

N/AWG - Number of Turns/Wire Size for Test Coil



Fair-Rite Product's Catalog Part Data Sheet, 2944777721 Printed: 2013-07-03








Ferrite Material Constants

Specific Heat 0.25 cal/g/°C 3.5 - 4.5 mW/cm - °C Thermal Conductivity Coefficient of Linear Expansion 8 - 10x10-6/°C Tensile Strength 4.9 kgf/mm² Compressive Strength 42 kgf/mm² 15x103 kgf/mm2 Young's Modulus Hardness (Knoop)..... 650 Specific Gravity $\approx 4.7 \text{ g/cm}^3$ The above quoted properties are typical for Fair-Rite MnZn and NiZn ferrites.

See next page for further material specifications.



Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

A NiZn ferrite developed to combine a high suppression performance, from 30 MHz to 500 MHz, with a very high dc resistivity.

SM beads, PC beads, wound beads, round cable snap-its, and connector EMI suppression plates are all available in 44 material.

Fair-Rite Product's Catalog Part Data Sheet, 2944777721

Printed: 2013-07-03










44 Material Characteristics:


Property	Unit	Symbol	Value
Initial Permeability @ B < 10 gauss		μ_{i}	500
Flux Density	gauss	В	3000
@ Field Strength	oersted	н	10
Residual Flux Density	gauss	B _r	1100
Coercive Force	oersted	H _c	0.45
Loss Factor	10-6	tan δ/μ	125
@ Frequency	MHz		1.0
Temperature Coefficient of Initial Permeability (20 -70°C)	%/°C		0.75
Curie Temperature	°C	T _o	>160
Resistivity	Ωcm	ρ	1x10°

Complex Permeability vs. Frequency




Measured on a 17/10/6mm toroid using the HP 4284A and the HP 4291A.

Initial Permeability vs. Temperature




Measured on a 17/10/6mm toroid at 100kHz.

Percent of Original Impedance vs. Temperature




Measured on a 2644000301 using the HP4291A.

Hysteresis Loop



Measured on a 17/10/6mm toroid at 10kHz.




Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

Fair-Rite Product's Catalog Part Data Sheet, 2944777721 Printed: 2013-07-03










Impedance, reactance, and resistance vs. frequency.



Impedance vs. frequency with dc bias.