Commercial Off-The-Shelf (COTS) for Higher Reliability Applications, X7R Dielectric, 6.3 – 250 VDC





Overview

KEMET's COTS program is an extension of KEMET knowledge of high reliability test regimes and requirements. KEMET regularly supplies "up-screened" products by working with customer drawings and imposing specified design and test requirements. The COTS program offers the same high quality and high reliability components as up-screened products, but at a lower cost to the customer. This is accomplished by eliminating the need for customer-specific drawings to achieve the reliability level required for customer applications. A series of tests and inspections have been selected to provide the accelerated conditioning and 100% screening necessary to eliminate infant mortal failures from the population.

KEMET's X7R dielectric features a 125°C maximum operating temperature and is considered "temperature stable." The Electronics Components, Assemblies & Materials Association (EIA) characterizes X7R dielectric as a Class II material. Components of this classification are fixed, ceramic dielectric capacitors suited for bypass and decoupling applications or for frequency discriminating circuits where Q and stability of capacitance characteristics are not critical. X7R exhibits a predictable change in capacitance with respect to time and voltage and boasts a minimal change in capacitance with reference to ambient temperature. Capacitance change is limited to ±15% from -55°C to +125°C.

All COTS testing includes voltage conditioning and post-electrical testing as per MIL–PRF–55681. For enhanced reliability, KEMET also provides the following test level options and conformance certifications:





Ordering Information

| С | 1210 | T | 104 | K | 5 | R | Α | С | TU |
|---------|--|--------------------------|--|---------------------------------|--|------------|--|---|---|
| Ceramic | Case Size (L" x W") | Specification/ Series | Capacitance Code (pF) | Capacitance Tolerance | Rated Voltage (VDC) | Dielectric | Failure Rate/Design | Termination Finish ¹ | Packaging/Grade (C-Spec) |
| | 0402 0603 0805 1206 1210 1812 2220 | T = COTS | Two significant digits + number of zeros | J = ±5% K = ±10% M = ±20% | 9 = 6.3 8 = 10 4 = 16 3 = 25 5 = 50 1 = 100 2 = 200 A = 250 | R = X7R | A = Testing per MIL-PRF- 55681 PDA 8% B= Testing per MIL-PRF- 55681 PDA 8%, DPA per EIA-469 C = Testing per MIL-PRF- 55681 PDA 8%, DPA per EIA- 469, Humidity per MIL-STD-202, Method 103, Condition A | C = 100% Matte Sn L = SnPb (5% Pb minimum) | See "Packaging C-Spec Ordering Options Table" below |

¹ Additional termination finish options may be available. Contact KEMET for details.



Packaging C-Spec Ordering Options Table

| Packaging Type ¹ | Packaging/Grade Ordering Code (C-Spec) |
|--|---|
| Bulk Bag/Unmarked | Not required (Blank) |
| 7" Reel/Unmarked | TU |
| 13" Reel/Unmarked | 7411 (EIA 0603 and smaller case sizes) 7210 (EIA 0805 and larger case sizes) |
| 7" Reel/Marked | TM |
| 13" Reel/Marked | 7040 (EIA 0603 and smaller case sizes) 7215 (EIA 0805 and larger case sizes) |
| 7" Reel/Unmarked/2mm pitch ² | 7081 |
| 13" Reel/Unmarked/2mm pitch ² | 7082 |

¹ Default packaging is "Bulk Bag". An ordering code C-Spec is not required for "Bulk Bag" packaging.

Benefits

- -55°C to +125°C operating temperature range
- · Lead (Pb)-Free, RoHS and REACH compliant
- Voltage conditioning and post-electrical testing per MIL–PRF– 55681
- Destructive Physical Analysis (DPA) per EIA–469
- Biased humidity testing (85/85) per MIL-STD-202
- · Certificate of Compliance
- Temperature stable dielectric
- EIA 0402, 0603, 0805, 1206, 1210, 1812, and 2220 case sizes

- DC voltage ratings of 6.3 V, 10 V, 16 V, 25 V, 50 V, 100 V, 200 V, and 250 V
- Capacitance offerings ranging from 10 pF to 22 μF
- Available capacitance tolerances of ±5%, ±10%, and ±20%
- · Non-polar device, minimizing installation concerns
- 100% pure matte tin-plated termination finish allowing for excellent solderability
- SnPb termination finish option available upon request (5% Pb minimum)

Applications


Typical applications include military, space quality and high reliability electronics.

¹ The terms "Marked" and "Unmarked" pertain to laser marking option of capacitors. All packaging options labeled as "Unmarked" will contain capacitors that have not been laser marked. Please contact KEMET if you require a laser marked option. For more information see "Capacitor Marking".

² The 2 mm pitch option allows for double the packaging quantity of capacitors on a given reel size. This option is limited to EIA 0603 (1608 metric) case size devices. For more information regarding 2 mm pitch option see "Tape & Reel Packaging Information".



Dimensions – Millimeters (Inches)



| EIA Size Code | Metric Size Code | L Length | W Width | T Thickness | B Bandwidth | S Separation Minimum | Mounting Technique |
|---------------------|------------------------|---------------------------|---------------------------|------------------------------|---------------------------|----------------------------|---------------------------------|
| 0402 | 1005 | 1.00 (.040) ± 0.05 (.002) | 0.50 (.020) ± 0.05 (.002) | | 0.30 (.012) ± 0.10 (.004) | 0.30 (.012) | Solder Reflow Only |
| 0603 | 1608 | 1.60 (.063) ± 0.15 (.006) | 0.80 (.032) ± 0.15 (.006) | | 0.35 (.014) ± 0.15 (.006) | 0.70 (.028) | |
| 0805 | 2012 | 2.00 (.079) ± 0.20 (.008) | 1.25 (.049) ± 0.20 (.008) | | 0.50 (0.02) ± 0.25 (.010) | 0.75 (.030) | Solder Wave or Solder Reflow |
| 1206 | 3216 | 3.20 (.126) ± 0.20 (.008) | 1.60 (.063) ± 0.20 (.008) | See Table 2 for Thickness | 0.50 (0.02) ± 0.25 (.010) | | |
| 1210¹ | 3225 | 3.20 (.126) ± 0.20 (.008) | 2.50 (.098) ± 0.20 (.008) | | 0.50 (0.02) ± 0.25 (.010) | N1/A | |
| 1812 | 4532 | 4.50 (.177) ± 0.30 (.012) | 3.20 (.126) ± 0.30 (.012) | | 0.60 (.024) ± 0.35 (.014) | N/A | Solder Reflow Only |
| 2220 | 5650 | 5.70 (.224) ± 0.40 (.016) | 5.00 (.197) ± 0.40 (.016) | | 0.60 (.024) ± 0.35 (.014) | | |

¹ For capacitance values ≥ 4.7 μ F add 0.02 (0.001) to the width tolerance dimension and 0.10 (0.004) to the length tolerance dimension.

Qualification/Certification

Commercial Grade products are subject to internal qualification. Details regarding test methods and conditions are referenced in Table 4, Performance & Reliability.

Environmental Compliance

Lead (Pb)-Free, RoHS, and REACH compliant without exemptions (excluding SnPb termination finish option).



Electrical Parameters/Characteristics

| Item | Parameters/Characteristics |
|--|---|
| Operating Temperature Range | -55°C to +125°C |
| Capacitance Change with Reference to +25°C and 0 Vdc Applied (TCC) | ±15% |
| ¹ Aging Rate (Maximum % Capacitance Loss/Decade Hour) | 3.0% |
| ² Dielectric Withstanding Voltage (DWV) | 250% of rated voltage (5 ± 1 seconds and charge/discharge not exceeding 50mA) |
| ³ Dissipation Factor (DF) Maximum Limit @ 25°C | 5%(6.3V & 10V), 3.5%(16V & 25V) and 2.5%(50V to 250V) |
| ⁴Insulation Resistance (IR) Minimum Limit @ 25°C | See Insulation Resistance Limit Table (Rated voltage applied for 120 ± 5 secs @ 25°C) |

Regarding Aging Rate: Capacitance measurements (including tolerance) are indexed to a referee time of 1,000 hours.

 $1kHz \pm 50Hz$ and 1.0 ± 0.2 Vrms if capacitance ≤ $10\mu F$

120Hz \pm 10Hz and 0.5 ± 0.1 Vrms if capacitance >10 μ F

Note: When measuring capacitance it is important to ensure the set voltage level is held constant. The HP4284 & Agilent E4980 have a feature known as Automatic Level Control (ALC). The ALC feature should be switched to "ON".

Post Environmental Limits

| | High Temperatu | ıre Life, Biased | Humidity, Moist | ture Resistance | |
|------------|---------------------|----------------------|--------------------------------|----------------------|--------------------------|
| Dielectric | Rated DC Voltage | Capacitance Value | Dissipation Factor (Maximum %) | Capacitance Shift | Insulation Resistance |
| | > 25 | | 3.0 | | |
| X7R | 16/25 | All | 5.0 | ±20% | 10% of Initial Limit |
| | < 16 | | 7.5 | | |

Insulation Resistance Limit Table

| EIA Case Size | 1,000 Megohm Microfarads or 100 GΩ | 500 Megohm Microfarads or 10 GΩ |
|---------------|---------------------------------------|------------------------------------|
| 0201 | N/A | ALL |
| 0402 | < 0.012 µF | ≥ 0.012 µF |
| 0603 | < 0.047 µF | ≥ 0.047 µF |
| 0805 | < 0.15 µF | ≥ 0.15 µF |
| 1206 | < 0.47 µF | ≥ 0.47 µF |
| 1210 | < 0.39 µF | ≥ 0.39 µF |
| 1808 | ALL | N/A |
| 1812 | < 2.2 μF | ≥ 2.2 µF |
| 1825 | ALL | N/A |
| 2220 | < 10 µF | ≥ 10 µF |
| 2225 | ALL | N/A |

²DWV is the voltage a capacitor can withstand (survive) for a short period of time. It exceeds the nominal and continuous working voltage of the capacitor.

³Capacitance and dissipation factor (DF) measured under the following conditions:

⁴To obtain IR limit, divide MΩ- μ F value by the capacitance and compare to GΩ limit. Select the lower of the two limits.



Table 1A – Capacitance Range/Selection Waterfall (0402 – 1206 Case Sizes)

| | | | se Si erie | | | CO | 402 | 2T | | | | CO | 603 | ВТ | | | | | (| C08 | 05T | • | | | | | (| C12 | 06T | • | | |
|---|--|--------------------|---------------------------------------|---------------------------------------|-----|----|------|----|----|--|--|---|---|---|---|---------------------------------------|---|----------------------------------|----------|--|--|--|--|--|---|--|--|--|--|--|--|-----|
| Capacitance | Сар | Volt | age C | ode | 9 | 8 | 4 | 3 | 5 | 9 | 8 | 4 | 3 | 5 | 1 | 2 | 9 | 8 | 4 | 3 | 5 | 1 | 2 | Α | 9 | 8 | 4 | 3 | 5 | 1 | 2 | Α |
| | Code | | ed Volt (VDC) | | 6.3 | 10 | 16 | 52 | 20 | 6.3 | 9 | 16 | 22 | 20 | 9 | 200 | 6.3 | 5 | 9 | 25 | 20 | 100 | 200 | 250 | 6.3 | 5 | 9 | 52 | 20 | ş | 700 | 250 |
| | | | acita | | | | | | | | | | | | | | bility or Ch | | | | | | | | | | | | | | J | |
| 100 – 150 pF** | 100 - 910* 101 - 151** 102 122 152 182 222 272 332 392 472 562 682 822 103 123 153 183 223 273 393 473 563 683 823 104 124 154 184 224 274 334 394 474 564 684 | | K K K K K K K K K K K K K K K K K K K | M M M M M M M M M M M M M M M M M M M | BB | BB | BB | BB | BB | CF C | CF C | CF CF CF CF CF CF CF CF CF CF CF CF CF C | CF CF CF CF CF CF CF CF CF CF CF CF CF C | CF CF CF CF CF CF CF CF CF CF CF CF CF C | CF CF CF CF CF CF CF CF CF CF CF CF CF C | C C C C C C C C C C C C C C C C C C C | D N N D N D N D N D N D N D N D N D N D | <u> </u> | | DN DN< | DN DN DN DN DN DN DN DN DN DN | DN D | DN D | DN D | EB E | EB E | EB E | EB E | EB E | EB E | EB E | |
| 0.82 µF 1.0 µF 1.2 µF 1.5 µF 1.8 µF 2.2 µF 3.3 µF 3.9 µF 4.7 µF 5.6 µF 6.8 µF | 824 105 125 155 185 225 275 335 395 475 565 685 |] | K K K K K K K K K K K K | M M M M M M M M | | | | | | | | | | | | | DG | DP DP DE DG DG DG | DG DG | DG DG | | | | | EF ED ED EN ED EF | EF ED ED EN ED EF EH EH | ED EN ED EF EF EH | EH | EH EH | | | |
| | | | ed Volt | tage | 6.3 | 10 | 16 | 25 | 50 | 6.3 | 9 | 16 | 25 | 20 | 100 | 200 | 6.3 | 9 | 16 | 25 | 50 | 100 | 200 | 250 | 6.3 | 9 | 9 | 25 | 20 | 100 | 200 | 250 |
| Capacitance | Cap Code | (VDC) Voltage Code | | | 9 | 8 | 4 | 3 | 5 | 9 | 8 | 4 | 3 | 5 | 1 | 2 | 9 | 8 | 4 | 3 | 5 | 1 | 2 | Α | 9 | 8 | 4 | 3 | 5 | 1 | 2 | Α |
| | | Ca | se Siz Series | ze/ | | C | 0402 | Т | | | | C | 0603 | Т | | | | 1 | | C08 | 05T | | | | | | | C12 | 06T | | | |

^{*}Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82 and 91)

^{**}Capacitance range Includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68 and 82)



Table 1A - Capacitance Range/Selection Waterfall (0402 - 1206 Case Sizes) cont'd

| | | Case Size/ Series | | CO |)402 | 2T | | | | C |)60 | 3T | | | | | (| C08 | 051 | | _ | | | | C | C12 | 06T | , | | |
|-----------------|------------|--------------------------|-----|----|------|----|----|-----|----|----|------|----|-----|-----|-----------------|---|----|-----|-----|-----|-----|-----|----------|----------|----|-----|-----|-----|-----|-----|
| Capacitance | Cap | Voltage Code | 9 | 8 | 4 | 3 | 5 | 9 | 8 | 4 | 3 | 5 | 1 | 2 | 9 | 8 | 4 | 3 | 5 | 1 | 2 | Α | 9 | 8 | 4 | 3 | 5 | 1 | 2 | Α |
| Oupacitance | Code | Rated Voltage (VDC) | 6.3 | 9 | 16 | 25 | 50 | 6.3 | 9 | 16 | 25 | 20 | 100 | 200 | 6.3 | 6 | 16 | 25 | 20 | 100 | 200 | 250 | 6.3 | 10 | 16 | 25 | 50 | 100 | 200 | 250 |
| | | Capacitance Tolerance | | | | | | | | | | | | | bility or Ch | | | | | | | | | | | | | | | |
| 8.2 μF 10 μF | 825 106 | J K M J K M | | | | | | | | | | | | | | | | | | | | | EH EH | EH EH | EH | | | | | |
| | Сар | Rated Voltage (VDC) | 6.3 | 10 | 16 | 25 | 50 | 6.3 | 10 | 16 | 25 | 20 | 100 | 200 | 6.3 | 9 | 16 | 25 | 20 | 100 | 200 | 250 | 6.3 | 10 | 16 | 22 | 50 | 100 | 200 | 250 |
| Capacitance | Code | Voltage Code | 9 | 8 | 4 | 3 | 5 | 9 | 8 | 4 | 3 | 5 | 1 | 2 | 9 | 8 | 4 | 3 | 5 | 1 | 2 | Α | 9 | 8 | 4 | 3 | 5 | 1 | 2 | Α |
| | Code _ | | | С | 0402 | T | | | | С | 0603 | Т | | | | | | C08 | 05T | | | | | | | C12 | 06T | | | |

^{*}Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82 and 91)

Table 1B - Capacitance Range/Selection Waterfall (1210 - 2220 Case Sizes)

| | | | se S erie | ize/ | | | | C12 | 10T | | | | C | 1808 | ВТ | | С | 1812 | 2T | | | C18 | 25T | | | C | 2220 |)T | |
|----------------|-------------|------|----------------|------|-----|----|----|-----|-----|-----|-----|-----|-------------|-------|---------------|---------|----------------|---------------|---------------|--------------|-----|-----|-----|-----|----|----|------|-----|-----|
| Canacitance | Con Codo | Volt | age C | ode | 9 | 8 | 4 | 3 | 5 | 1 | 2 | Α | 5 | 1 | 2 | 3 | 5 | 1 | 2 | Α | 5 | 1 | 2 | Α | 3 | 5 | 1 | 2 | Α |
| Capacitance | Cap Code | Rate | d Vol | | 6.3 | 9 | 16 | 25 | 20 | 100 | 200 | 250 | 20 | 100 | 200 | 25 | 20 | 100 | 200 | 250 | 20 | 100 | 200 | 250 | 25 | 20 | 100 | 200 | 250 |
| | | | acita Ieran | | | | | | | | | Pi | rodu See | t Ava | ailab 2 fo | ility a | and C p Thi | hip T ckne | hick ss Di | ness mens | Cod | es | | | | | | | |
| 10 - 91 pF* | 100 - 910* | J | K | M | FB | FB | FB | FB | FB | FB | FB | | | | | | | | | | | | | | | | | | |
| 100 - 270 pF** | 101 - 391** | J | K | M | FB | FB | FB | FB | FB | FB | FB | | | | | | | | | | | | | | | | | | |
| 330 pF | 331 | J | K | M | FB | FB | FB | FB | FB | FB | FB | | LF | LF | LF | | | | | | | | | | | | | | |
| 390 pF | 391 | J | K | M | FB | FB | FB | FB | FB | FB | FB | | LF | LF | LF | | | | | | | | | | | | | | |
| 470 - 820 pF** | 471 - 821** | J | K | M | FB | FB | FB | FB | FB | FB | FB | | LF | LF | LF | GB | GB | GB | GB | | | | | | | | | | |
| 1,000 pF | 102 | J | K | M | FB | FB | FB | FB | FB | FB | FB | | LF | LF | LF | GB | GB | GB | GB | | | | | | | | | | |
| 1,200 pF | 122 | J | K | M | FB | FB | FB | FB | FB | FB | FB | | LF | LF | LF | GB | GB | GB | GB | | | | | | | | | | |
| 1,500 pF | 152 | J | K | M | FB | FB | FB | FB | FB | FB | FE | | LF | LF | LF | GB | GB | GB | GB | | | | | | | | | | |
| 1,800 pF | 182 | J | K | M | FB | FB | FB | FB | FB | FB | FE | | LF | LF | LF | GB | GB | GB | GB | | | | | | | | | | |
| 2,200 pF | 222 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LF | LF | LF | GB | GB | GB | GB | | | | | | | | | | |
| 2,700 pF | 272 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LF | LF | LF | GB | GB | GB | GB | | | | | | | | | | |
| 3,300 pF | 332 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LF | LF | | GB | GB | GB | GB | | | | | | | | | | |
| 3,900 pF | 392 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LF | LF | l | GB | GB | GB | GB | | | | | | | | | | |
| 4,700 pF | 472 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LD | LD | | GB | GB | GB | GD | | | | | | | | | | |
| 5,600 pF | 562 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LD | LD | | GB | GB | GB | GH | | | | | | | | | | |
| 6,800 pF | 682 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LD | LD | | GB | GB | GB | GB | GB | | | | | JE | JE | JE | | |
| 8,200 pF | 822 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LD | LD | l | GB | GB | GB | GB | GB | | | | | JE | JE | JE | | |
| 10,000 pF | 103 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LD | LD | İ | GB | GB | GB | GB | GB | | | | | JE | JE | JE | | |
| 12,000 pF | 123 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LD | LD | İ | GB | GB | GB | GB | GB | | | | | JE | JE | JE | | |
| 15,000 pF | 153 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LD | LD | İ | GB | GB | GB | GB | GB | İ | | | | JE | JE | JE | | |
| 18,000 pF | 183 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LD | LD | İ | GB | GB | GB | GB | GB | | | | | JE | JE | JE | | |
| 22,000 pF | 223 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LD | LD | İ | GB | GB | GB | GB | GB | НВ | НВ | HB | НВ | JE | JE | JE | | |
| 27,000 pF | 273 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LD | LD | İ | GB | GB | GB | GB | GB | НВ | НВ | НВ | НВ | JE | JE | JE | | |
| | | | d Vol | | 6.3 | 10 | 16 | 25 | 20 | 100 | 200 | 250 | 20 | 100 | 200 | 25 | 20 | 100 | 200 | 250 | 50 | 100 | 200 | 250 | 25 | 50 | 100 | 200 | 250 |
| Capacitance | Cap Code | Volt | age C | ode | 9 | 8 | 4 | 3 | 5 | 1 | 2 | Α | 5 | 1 | 2 | 3 | 5 | 1 | 2 | Α | 5 | 1 | 2 | Α | 3 | 5 | 1 | 2 | Α |
| | Code | | se Si Serie | | | | | C12 | 10T | | | | C | 1808 | Т | | C | 1812 | T | | | C18 | 25T | | | С | 2220 | т | |

^{*}Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82 and 91)

^{**}Capacitance range Includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68 and 82)

^{**}Capacitance range Includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68 and 82)



Table 1B - Capacitance Range/Selection Waterfall (1210 - 2220 Case Sizes) cont'd

| | | | se S erie | ize/ | | | | C12 | :10T | | | | C | 1808 | ВТ | | С | 1812 | 2T | | | C18 | 3251 | • | | C | 222(|)T | |
|--------------------|------------|------|-----------------|--------|-----|----|----------|----------|----------|----------|------|------|------|-------|-------|---------|-------|----------|----------------|------|--------------|-----|------|-----|----|-----|------|-----|-----|
| Capacitance | Can Code | Volt | age C | ode | 9 | 8 | 4 | 3 | 5 | 1 | 2 | Α | 5 | 1 | 2 | 3 | 5 | 1 | 2 | Α | 5 | 1 | 2 | Α | 3 | 5 | 1 | 2 | Α |
| Oupuonunce | Cap Coue | | ed Vol (VDC) |) | 6.3 | 10 | 16 | 25 | 20 | 100 | 200 | 250 | 20 | 100 | 200 | 25 | 20 | 100 | 200 | 250 | 50 | 100 | 200 | 250 | 25 | 20 | 100 | 200 | 250 |
| | | | acita Ieran | | | | | | | | | Pi | rodu | t Ava | ailab | ility a | and C | hip 1 | Thick ss Di | ness | Code | es | | | | | | | |
| 33,000 pF | 333 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LD | LD | 2 101 | GB | GB | GB | GB | GB | HB | НВ | НВ | НВ | JB | JB | JB | | |
| 39,000 pF | 393 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LD | LD | | GB | GB | GB | GB | GB | НВ | НВ | НВ | НВ | JB | JB | JB | | |
| 47,000 pF | 473 | J | K | M | FB | FB | FB | FB | FB | FB | FB | FB | LD | LD | | GB | GB | GB | GB | GB | НВ | НВ | НВ | НВ | JB | JB | JB | | |
| 56,000 pF | 563 | Ĵ | K | M | FB | FB | FB | FB | FB | FB | FC | FC | LD | LD | | GB | GB | GB | GB | GB | НВ | НВ | НВ | НВ | JB | JB | JB | | |
| 68,000 pF | 683 | J | K | M | FB | FB | FB | FB | FB | FB | FC | FC | LD | | | GB | GB | GB | GB | GB | НВ | НВ | НВ | НВ | JB | JB | JB | | |
| 82,000 pF | 823 | J | K | M | FB | FB | FB | FB | FB | FC | FF | FF | LD | | | GB | GB | GB | GB | GB | НВ | НВ | НВ | НВ | JB | JB | JC | JC | JC |
| 0.10 µF | 104 | Ĵ | K | M | FB | FB | FB | FB | FB | FD | FG | FG | LD | | | GB | GB | GB | GB | GB | НВ | НВ | НВ | НВ | JB | JB | JC | JC | JC |
| 0.10 µF | 124 | J | K | M | FB | FB | FB | FB | FB | FD | FH | FH | LD | | | GB | GB | GB | GB | GB | НВ | HB | НВ | HB | JB | JB | JC | JC | JC |
| 0.12 μΓ 0.15 μF | 154 | J | K | M | FC | FC | FC | FC | FC | FD | FM | FM | LD | | | GB | GB | GB | GE | GE | HB | HB | HB | HB | JB | JB | JC | JC | JC |
| 0.18 µF | 184 | J | K | M | FC | FC | FC | FC | FC | FD | FK | FK | LD | | | GB | GB | GB | GG | GG | HB | HB | HB | HB | JB | JB | JC | JC | JC |
| 0.10 μl 0.22 μF | 224 | J | K | M | FC | FC | FC | FC | FC | FD | FK | FK | LD | | | GB | GB | GB | GG | GG | НВ | HB | HB | HB | JB | JB | JC | JC | JC |
| 0.22 μΓ 0.27 μF | 274 | J | K | M | FC | FC | FC | FC | FC | FD | I IX | I IX | | | | GB | GB | GG | GG | GG | НВ | HB | HB | HB | JC | JC | JC | JC | JC |
| 0.27 µF 0.33 µF | 334 | J | K | M | FD | FD | FD | FD | FD | FD | | | | | | GB | GB | GG | GG | GG | НВ | НВ | НВ | НВ | JC | JC | JC | JC | JC |
| 0.33 μF 0.39 μF | 394 | J | K | M | FD | FD | FD | FD | FD | FD | | | | | | GB | GB | GG | GG | GG | HD | HD | HD | HD | JC | JC | JC | JC | JC |
| | 394 474 | | | | FD | FD | | | | | | | l | | | GB | GB | | | | | | 1 | 1 | | JC | JC | JC | JC |
| 0.47 µF | 474 564 | J | K | M M | FD | FD | FD FD | FD FD | FD FD | FD FF | | | | | | GC | GC | GG GG | GJ | GJ | HD | HD | HD | HD | JC | JD | JD | JD | JD |
| 0.56 µF | | J | K | M | FD | | | | | FG | | | | | | | | | | | | | | | | 1 - | 1 - | | 1 ' |
| 0.68 µF | 684 | J | K | | | FD | FD | FD | FD | _ | | | | | | GC | GC | GG | | | HD | HD | HD | HD | JC | JD | JD | JD | JD |
| 0.82 µF | 824 | J | K | M | FF | FF | FF | FF | FF | FL | | | | | | GE | GE | GG | | | HF | HF | HF | HF | JC | JF | JF | JF | JF |
| 1.0 µF | 105 | J | K | M | FH | FH | FH | FH | FH | FM | | | | | | GE | GE | GG | | | HF | HF | HF | HF | JC | JF | JF | JF | JF |
| 1.2 µF | 125 | J | K | M | FH | FH | FH | FH | FG | | | | | | | | | | | | ļ. | | | | JC | JC | | | |
| 1.5 µF | 155 | J | K | M | FH | FH | FH | FH | FG | | | | | | | | | | | | | | | | JC | JC | | | |
| 1.8 µF | 185 | J | K | M | FH | FH | FH | FH | FG | | | | | | | | | | | | | | | | JD | JD | | | |
| 2.2 µF | 225 | J | K | M | FJ | FJ | FJ | FJ | FG | | | | | | | GO | GO | | | | | | | | JF | JF | | | |
| 2.7 µF | 275 | J | K | M | FE | FE | FE | FG | FH | | | | | | | | | | | | | | | | l | | | | |
| 3.3 µF | 335 | J | K | M | FF | FF | FF | FM | FM | | | | | | | • | | | | | | | | | | | | | |
| 3.9 µF | 395 | J | K | M | FG | FG | FG | FG | FK | | | | | | | | | | | | 1 | | | | | | | | |
| 4.7 µF | 475 | J | K | M | FC | FC | FC | FG | FS | | | | | | | GK | GK | | | | | | | | JF | JF | | | |
| 5.6 µF | 565 | J | K | M | FF | FF | FF | FH | | | | | | | | | | | | | | | | | | | | | |
| 6.8 µF | 685 | J | K | M | FG | FG | FG | FM | | | | | | | | | | | | | | | | | | | | | |
| 8.2 µF | 825 | J | K | M | FH | FH | FH | FK | | | | | | | | | | | | | | | | | | | | | |
| 10 μF | 106 | J | K | M | FH | FH | FH | FS | | | | | | | | GK | | | | | | | | | JF | JO | | | |
| 12 µF | 126 | J | K | M | | | | | | | | | | | | | | | | | | | | | | | | | |
| 15 µF | 156 | J | K | M | | | | | | | | | | | | | | | | | | | | | JO | | | | |
| 18 µF | 186 | J | K | M | | | | | | | | | | | | | | | | | | | | | | | | | |
| 22 µF | 226 | J | K | M | FS | FS | | | | | | | | | | | | | | | $oxed{oxed}$ | | | | JO | | | | |
| | | | ed Vol | | 6.3 | 9 | 16 | 25 | 20 | 100 | 200 | 250 | 50 | 100 | 200 | 25 | 50 | 100 | 200 | 250 | 50 | 100 | 200 | 250 | 25 | 50 | 100 | 200 | 250 |
| Capacitance | Cap | Volt | age C | ode | 9 | 8 | 4 | 3 | 5 | 1 | 2 | Α | 5 | 1 | 2 | 3 | 5 | 1 | 2 | Α | 5 | 1 | 2 | Α | 3 | 5 | 1 | 2 | Α |
| | Code | Ca | se Si Serie | ze/ | | | | C12 | 10T | | | | c | 1808 | | | | | | | | C18 | 325T | | | C | 2220 | | |

^{*}Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82 and 91)

^{**}Capacitance range Includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68 and 82)



Table 2A – Chip Thickness/Tape & Reel Packaging Quantities

| Thickness | Case | Thickness ± | Paper C | luantity ¹ | Plastic (| Quantity |
|----------------------------------|--|--|--|---|--|--|
| Code | Size ¹ | Range (mm) | 7" Reel | 13" Reel | 7" Reel | 13" Reel |
| BB CF DN DP DE | 0402 0603 0805 0805 0805 | 0.50 ± 0.05 0.80 ± 0.07 0.78 ± 0.10 0.90 ± 0.10 1.00 ± 0.10 | 10,000 4,000 4,000 4,000 0 | 50,000 15,000 15,000 15,000 0 | 0 0 0 0 2,500 | 0 0 0 0 10,000 |
| DG DH EB EC EN | 0805 0805 1206 1206 1206 | 1.25 ± 0.15 1.25 ± 0.20 0.78 ± 0.10 0.90 ± 0.10 0.95 ± 0.10 | 0 0 4,000 0 0 | 0 0 10,000 0 0 | 2,500 2,500 4,000 4,000 4,000 | 10,000 10,000 10,000 10,000 10,000 |
| ED EE EF EM EG EH | 1206 1206 1206 1206 1206 1206 | 1.00 ± 0.10 1.10 ± 0.10 1.20 ± 0.15 1.25 ± 0.15 1.60 ± 0.15 | 0 0 0 0 | 0 0 0 0 | 2,500 2,500 2,500 2,500 2,000 2,000 | 10,000 10,000 10,000 10,000 8,000 8,000 |
| FB FC FD FE FF | 1210 1210 1210 1210 1210 1210 | 1.60 ± 0.20 0.78 ± 0.10 0.90 ± 0.10 0.95 ± 0.10 1.00 ± 0.10 1.10 ± 0.10 | 0 0 0 0 0 | 0 0 0 0 0 | 4,000 4,000 4,000 4,000 2,500 2,500 | 0,000 10,000 10,000 10,000 10,000 |
| FG FL FH FM | 1210 1210 1210 1210 | 1.25 ± 0.15 1.40 ± 0.15 1.55 ± 0.15 1.70 ± 0.20 | 0 0 0 0 | 0 0 0 0 | 2,500 2,000 2,000 2,000 | 10,000 8,000 8,000 8,000 |
| FJ FK FS LD LF | 1210 1210 1210 1808 1808 | 1.85 ± 0.20 2.10 ± 0.20 2.50 ± 0.30 0.90 ± 0.10 1.00 ± 0.15 | 0 0 0 0 0 | 0 0 0 0 | 2,000 2,000 1,000 2,500 2,500 | 8,000 8,000 4,000 10,000 10,000 |
| GB GC GD GE GH | 1812 1812 1812 1812 1812 | 1.00 ± 0.10 1.10 ± 0.10 1.25 ± 0.15 1.30 ± 0.10 1.40 ± 0.15 | 0 0 0 0 0 | 0 0 0 0 0 | 1,000 1,000 1,000 1,000 1,000 | 4,000 4,000 4,000 4,000 4,000 |
| GG GK GJ GO HB | 1812 1812 1812 1812 1825 | 1.55 ± 0.10 1.60 ± 0.20 1.70 ± 0.15 2.50 ± 0.20 1.10 ± 0.15 | 0 0 0 0 | 0 0 0 0 | 1,000 1,000 1,000 500 1,000 | 4,000 4,000 4,000 2,000 4,000 |
| HD HF JB JC JD | 1825 1825 2220 2220 2220 | 1.30 ± 0.15 1.50 ± 0.15 1.00 ± 0.15 1.10 ± 0.15 1.30 ± 0.15 | 0 0 0 0 0 | 0 0 0 0 0 | 1,000 1,000 1,000 1,000 1,000 | 4,000 4,000 4,000 4,000 4,000 |
| JE JF JO | 2220 2220 2220 | 1.40 ± 0.15 1.50 ± 0.15 2.40 ± 0.15 | 0 0 0 | 0 0 0 | 1,000 1,000 500 | 4,000 4,000 2,000 |
| Thickness | Case | Thickness ± | 7" Reel | 13" Reel | 7" Reel | 13" Reel |
| Code | Size ¹ | Range (mm) | Paper C | luantity ¹ | Plastic (| Quantity |

Package quantity based on finished chip thickness specifications.

¹ If ordering using the 2 mm Tape and Reel pitch option, the packaging quantity outlined in the table above will be doubled. This option is limited to EIA 0603 (1608 metric) case size devices. For more information regarding 2 mm pitch option see "Tape & Reel Packaging Information".



Table 2B - Bulk Packaging Quantities

| Doolee | ulu u Tuu o | Loose Pa | ackaging |
|----------|------------------------|------------------------|-------------------------|
| Раска | ging Type | Bulk Bag | (default) |
| Packagi | ng C-Spec ¹ | N/ | /A ² |
| Cas | e Size | Packaging Quantities (| (pieces/unit packaging) |
| EIA (in) | Metric (mm) | Minimum | Maximum |
| 0402 | 1005 | | |
| 0603 | 1608 | | |
| 0805 | 2012 | | 50,000 |
| 1206 | 3216 | | |
| 1210 | 3225 | 1 | |
| 1808 | 4520 | | |
| 1812 | 4532 | | |
| 1825 | 4564 | | 20,000 |
| 2220 | 5650 | | |
| 2225 | 5664 | | |

¹ The "Packaging C-Spec" is a 4 to 8 digit code which identifies the packaging type and/or product grade. When ordering, the proper code must be included in the 15th through 22nd character positions of the ordering code. See "Ordering Information" section of this document for further details. Commercial Grade product ordered without a packaging C-Spec will default to our standard "Bulk Bag" packaging. Contact KEMET if you require a bulk bag packaging option for Automotive Grade products.

² A packaging C-Spec (see note 1 above) is not required for "Bulk Bag" packaging (excluding Anti-Static Bulk Bag and Automotive Grade products). The 15th through 22nd character positions of the ordering code should be left blank. All product ordered without a packaging C-Spec will default to out standard "Bulk Bag" packaging.



Table 3 - Chip Capacitor Land Pattern Design Recommendations per IPC-7351


| EIA Metric Size Size Code Code | | Density Level A: Maximum (Most) Land Protrusion (mm) | | | Density Level B: Median (Nominal) Land Protrusion (mm) | | | Density Level C: Minimum (Least) Land Protrusion (mm) | | | | | | | | |
|--------------------------------------|------|--|------|------|--|------|------|---|------|------|------|------|------|------|------|------|
| Oode | Oode | С | Y | X | V1 | V2 | С | Y | X | V1 | V2 | С | Y | X | V1 | V2 |
| 0402 | 1005 | 0.50 | 0.72 | 0.72 | 2.20 | 1.20 | 0.45 | 0.62 | 0.62 | 1.90 | 1.00 | 0.40 | 0.52 | 0.52 | 1.60 | 0.80 |
| 0603 | 1608 | 0.90 | 1.15 | 1.10 | 4.00 | 2.10 | 0.80 | 0.95 | 1.00 | 3.10 | 1.50 | 0.60 | 0.75 | 0.90 | 2.40 | 1.20 |
| 0805 | 2012 | 1.00 | 1.35 | 1.55 | 4.40 | 2.60 | 0.90 | 1.15 | 1.45 | 3.50 | 2.00 | 0.75 | 0.95 | 1.35 | 2.80 | 1.70 |
| 1206 | 3216 | 1.60 | 1.35 | 1.90 | 5.60 | 2.90 | 1.50 | 1.15 | 1.80 | 4.70 | 2.30 | 1.40 | 0.95 | 1.70 | 4.00 | 2.00 |
| 1210 | 3225 | 1.60 | 1.35 | 2.80 | 5.65 | 3.80 | 1.50 | 1.15 | 2.70 | 4.70 | 3.20 | 1.40 | 0.95 | 2.60 | 4.00 | 2.90 |
| 1210¹ | 3225 | 1.50 | 1.60 | 2.90 | 5.60 | 3.90 | 1.40 | 1.40 | 2.80 | 4.70 | 3.30 | 1.30 | 1.20 | 2.70 | 4.00 | 3.00 |
| 1812 | 4532 | 2.15 | 1.60 | 3.60 | 6.90 | 4.60 | 2.05 | 1.40 | 3.50 | 6.00 | 4.00 | 1.95 | 1.20 | 3.40 | 5.30 | 3.70 |
| 2220 | 5650 | 2.75 | 1.70 | 5.50 | 8.20 | 6.50 | 2.65 | 1.50 | 5.40 | 7.30 | 5.90 | 2.55 | 1.30 | 5.30 | 6.60 | 5.60 |

¹ Only for capacitance values ≥ 22 μF

Density Level A: For low-density product applications. Recommended for wave solder applications and provides a wider process window for reflow solder processes. KEMET only recommends wave soldering of EIA 0603, 0805, and 1206 case sizes.

Density Level B: For products with a moderate level of component density. Provides a robust solder attachment condition for reflow solder processes. **Density Level C:** For high component density product applications. Before adapting the minimum land pattern variations the user should perform qualification testing based on the conditions outlined in IPC Standard 7351 (IPC–7351).

Image below based on Density Level B for an EIA 1210 case size.





Soldering Process


Recommended Soldering Technique:

- Solder wave or solder reflow for EIA case sizes 0603, 0805 and 1206
- · All other EIA case sizes are limited to solder reflow only

Recommended Reflow Soldering Profile:

KEMET's families of surface mount multilayer ceramic capacitors (SMD MLCCs) are compatible with wave (single or dual), convection, IR or vapor phase reflow techniques. Preheating of these components is recommended to avoid extreme thermal stress. KEMET's recommended profile conditions for convection and IR reflow reflect the profile conditions of the IPC/J-STD-020 standard for moisture sensitivity testing. These devices can safely withstand a maximum of three reflow passes at these conditions.

| Profile Feature | Termination Finish | | | |
|--|--------------------|--------------------|--|--|
| Profile realure | SnPb | 100% Matte Sn | | |
| Preheat/Soak | | | | |
| Temperature Minimum (T _{Smin}) | 100°C | 150°C | | |
| Temperature Maximum (T _{Smax}) | 150°C | 200°C | | |
| Time (t_s) from T_{smin} to T_{smax} | 60 – 120 seconds | 60 – 120 seconds | | |
| Ramp-Up Rate (T _L to T _P) | 3°C/second maximum | 3°C/second maximum | | |
| Liquidous Temperature (T _L) | 183°C | 217°C | | |
| Time Above Liquidous (t _L) | 60 – 150 seconds | 60 – 150 seconds | | |
| Peak Temperature (T _P) | 235°C | 260°C | | |
| Time Within 5°C of Maximum Peak Temperature (t _P) | 20 seconds maximum | 30 seconds maximum | | |
| Ramp-Down Rate (T _P to T _L) | 6°C/second maximum | 6°C/second maximum | | |
| Time 25°C to Peak Temperature | 6 minutes maximum | 8 minutes maximum | | |








Table 4 – Performance & Reliability: Test Methods and Conditions


| Stress | Reference | Test or Inspection Method | | | |
|------------------------|------------------------------------|---|--|--|--|
| Terminal Strength | JIS-C-6429 | Appendix 1, Note: Force of 1.8 kg for 60 seconds. | | | |
| Board Flex | JIS-C-6429 | Appendix 2, Note: Standard termination system – 2.0 mm (minimum) for all except 3 mm for C0G. Flexible termination system – 3.0 mm (minimum). | | | |
| | | Magnification 50 X. Conditions: | | | |
| Solderability | J-STD-002 | a) Method B, 4 hours @ 155°C, dry heat @ 235°C | | | |
| Soluerability | J-31D-002 | b) Method B @ 215°C category 3 | | | |
| | | c) Method D, category 3 @ 260°C | | | |
| Temperature Cycling | JESD22 Method JA-104 | 1,000 Cycles (-55°C to +125°C). Measurement at 24 hours +/- 4 hours after test conclusion. | | | |
| Biased Humidity | MIL-STD-202 Method 103 | Load Humidity: 1,000 hours 85°C/85% RH and rated voltage. Add 100 K ohm resistor. Measurement at 24 hours +/- 4 hours after test conclusion. Low Volt Humidity: 1,000 hours 85°C/85% RH and 1.5 V. Add 100 K ohm resistor. Measurement at 24 hours +/- 4 hours after test conclusion. | | | |
| Moisture Resistance | MIL-STD-202 Method 106 | t = 24 hours/cycle. Steps 7a and 7b not required. Measurement at 24 hours +/- 4 hours after test conclusion. | | | |
| Thermal Shock | MIL-STD-202 Method 107 | -55°C/+125°C. Note: Number of cycles required – 300, maximum transfer time – 20 seconds, dwell time – 15 minutes. Air – Air. | | | |
| High Temperature Life | MIL-STD-202 Method 108 /EIA-198 | 1,000 hours at 125°C (85°C for X5R, Z5U and Y5V) with 2 X rated voltage applied. | | | |
| Storage Life | MIL-STD-202 Method 108 | 150°C, 0 VDC for 1,000 hours. | | | |
| Vibration | MIL-STD-202 Method 204 | 5 g's for 20 min., 12 cycles each of 3 orientations. Note: Use 8" X 5" PCB 0.031" thick 7 secure points on one long side and 2 secure points at corners of opposite sides. Parts mounted within 2" from any secure point. Test from 10 – 2,000 Hz | | | |
| Mechanical Shock | MIL-STD-202 Method 213 | Figure 1 of Method 213, Condition F. | | | |
| Resistance to Solvents | MIL-STD-202 Method 215 | Add aqueous wash chemical, OKEM Clean or equivalent. | | | |

Storage & Handling

Ceramic chip capacitors should be stored in normal working environments. While the chips themselves are quite robust in other environments, solderability will be degraded by exposure to high temperatures, high humidity, corrosive atmospheres, and long term storage. In addition, packaging materials will be degraded by high temperature—reels may soften or warp and tape peel force may increase. KEMET recommends that maximum storage temperature not exceed 40°C and maximum storage humidity not exceed 70% relative humidity. Temperature fluctuations should be minimized to avoid condensation on the parts and atmospheres should be free of chlorine and sulfur bearing compounds. For optimized solderability chip stock should be used promptly, preferably within 1.5 years of receipt.



Construction





Capacitor Marking (Optional):

These surface mount multilayer ceramic capacitors are normally supplied unmarked. If required, they can be marked as an extra cost option. Marking is available on most KEMET devices but must be requested using the correct ordering code identifier(s). If this option is requested, two sides of the ceramic body will be laser marked with a "K" to identify KEMET, followed by two characters (per EIA–198 - see table below) to identify the capacitance value. EIA 0603 case size devices are limited to the "K" character only.

Laser marking option is <u>not</u> available on:

- C0G, Ultra Stable X8R and Y5V dielectric devices
- EIA 0402 case size devices
- EIA 0603 case size devices with Flexible Termination option.
- · KPS Commercial and Automotive Grade stacked devices.
- · X7R dielectric products in capacitance values outlined below

| EIA Case Size | Metric Size Code | Capacitance |
|---------------|-------------------------|-------------|
| 0603 | 1608 | ≤ 170 pF |
| 0805 | 2012 | ≤ 150 pF |
| 1206 | 3216 | ≤ 910 pF |
| 1210 | 3225 | ≤ 2,000 pF |
| 1808 | 4520 | ≤ 3,900 pF |
| 1812 | 4532 | ≤ 6,700 pF |
| 1825 | 4564 | ≤ 0.018 µF |
| 2220 | 5650 | ≤ 0.027 µF |
| 2225 | 5664 | ≤ 0.033 µF |

Marking appears in legible contrast. Illustrated below is an example of an MLCC with laser marking of "KA8", which designates a KEMET device with rated capacitance of 100 μ F. Orientation of marking is vendor optional.





Capacitor Marking (Optional) cont'd

| | Capacitance (pF) For Various Alpha/Numeral Identifiers | | | | | | | | | | | | |
|-----------|--|------------------|--|-----|-------|--------|---------|-----------|------------|-------------|--|--|--|
| | | | The state of the s | | | Numera | | | | | | | |
| Alpha | 9 | 0 | 1 | 2 | 3 | 4 | 5 | 6 | 7 | 8 | | | |
| Character | | Capacitance (pF) | | | | | | | | | | | |
| Α | 0.1 | 10 | 10 | 100 | 1,000 | 10,000 | 100,000 | 1,000,000 | 10,000,000 | 100,000,000 | | | |
| В | 0.11 | 1.1 | 11 | 110 | 1,100 | 11,000 | 110,000 | 1,100,000 | 11,000,000 | 110,000,000 | | | |
| С | 0.12 | 12 | 12 | 120 | 1,200 | 12,000 | 120,000 | 1,200,000 | 12,000,000 | 120,000,000 | | | |
| D | 0.13 | 13 | 13 | 130 | 1,300 | 13,000 | 130,000 | 1,300,000 | 13,000,000 | 130,000,000 | | | |
| Е | 0.15 | 15 | 15 | 150 | 1,500 | 15,000 | 150,000 | 1,500,000 | 15,000,000 | 150,000,000 | | | |
| F | 0.16 | 16 | 16 | 160 | 1,600 | 16,000 | 160,000 | 1,600,000 | 16,000,000 | 160,000,000 | | | |
| G | 0.18 | 18 | 18 | 180 | 1,800 | 18,000 | 180,000 | 1,800,000 | 18,000,000 | 180,000,000 | | | |
| Н | 0.2 | 20 | 20 | 200 | 2,000 | 20,000 | 200,000 | 2,000,000 | 20,000,000 | 200,000,000 | | | |
| J | 0.22 | 22 | 22 | 220 | 2,200 | 22,000 | 220,000 | 2,200,000 | 22,000,000 | 220,000,000 | | | |
| К | 0.24 | 2.4 | 24 | 240 | 2,400 | 24,000 | 240,000 | 2,400,000 | 24,000,000 | 240,000,000 | | | |
| L | 0.27 | 2.7 | 27 | 270 | 2,700 | 27,000 | 270,000 | 2,700,000 | 27,000,000 | 270,000,000 | | | |
| M | 0.3 | 30 | 30 | 300 | 3,000 | 30,000 | 300,000 | 3,000,000 | 30,000,000 | 300,000,000 | | | |
| N | 0.33 | 33 | 33 | 330 | 3,300 | 33,000 | 330,000 | 3,300,000 | 33,000,000 | 330,000,000 | | | |
| Р | 0.36 | 36 | 36 | 360 | 3,600 | 36,000 | 360,000 | 3,600,000 | 36,000,000 | 360,000,000 | | | |
| Q | 0.39 | 39 | 39 | 390 | 3,900 | 39,000 | 390,000 | 3,900,000 | 39,000,000 | 390,000,000 | | | |
| R | 0.43 | 4 3 | 43 | 430 | 4,300 | 43,000 | 430,000 | 4,300,000 | 43,000,000 | 430,000,000 | | | |
| S | 0.47 | 4.7 | 47 | 470 | 4,700 | 47,000 | 470,000 | 4,700,000 | 47,000,000 | 470,000,000 | | | |
| Т | 0.51 | 5.1 | 51 | 510 | 5,100 | 51,000 | 510,000 | 5,100,000 | 51,000,000 | 510,000,000 | | | |
| U | 0.56 | 56 | 56 | 560 | 5,600 | 56,000 | 560,000 | 5,600,000 | 56,000,000 | 560,000,000 | | | |
| V | 0.62 | 62 | 62 | 620 | 6,200 | 62,000 | 620,000 | 6,200,000 | 62,000,000 | 620,000,000 | | | |
| W | 0.68 | 68 | 68 | 680 | 6,800 | 68,000 | 680,000 | 6,800,000 | 68,000,000 | 680,000,000 | | | |
| Х | 0.75 | 7 5 | 75 | 750 | 7,500 | 75,000 | 750,000 | 7,500,000 | 75,000,000 | 750,000,000 | | | |
| Υ | 0.82 | 82 | 82 | 820 | 8,200 | 82,000 | 820,000 | 8,200,000 | 82,000,000 | 820,000,000 | | | |
| Z | 0.91 | 9.1 | 91 | 910 | 9,100 | 91,000 | 910,000 | 9,100,000 | 91,000,000 | 910,000,000 | | | |
| а | 0.25 | 25 | 25 | 250 | 2,500 | 25,000 | 250,000 | 2,500,000 | 25,000,000 | 250,000,000 | | | |
| b | 0.35 | 35 | 35 | 350 | 3,500 | 35,000 | 350,000 | 3,500,000 | 35,000,000 | 350,000,000 | | | |
| d | 0.4 | 4 0 | 40 | 400 | 4,000 | 40,000 | 400,000 | 4,000,000 | 40,000,000 | 400,000,000 | | | |
| е | 0.45 | 4 5 | 45 | 450 | 4,500 | 45,000 | 450,000 | 4,500,000 | 45,000,000 | 450,000,000 | | | |
| f | 0.5 | 50 | 50 | 500 | 5,000 | 50,000 | 500,000 | 5,000,000 | 50,000,000 | 500,000,000 | | | |
| m | 0.6 | 60 | 60 | 600 | 6,000 | 60,000 | 600,000 | 6,000,000 | 60,000,000 | 600,000,000 | | | |
| n | 0.7 | 70 | 70 | 700 | 7,000 | 70,000 | 700,000 | 7,000,000 | 70,000,000 | 700,000,000 | | | |
| t | 0.8 | 8 0 | 80 | 800 | 8,000 | 80,000 | 800,000 | 8,000,000 | 80,000,000 | 800,000,000 | | | |
| у | 0.9 | 90 | 90 | 900 | 9,000 | 90,000 | 900,000 | 9,000,000 | 90,000,000 | 900,000,000 | | | |



Tape & Reel Packaging Information

KEMET offers multilayer ceramic chip capacitors packaged in 8, 12 and 16 mm tape on 7" and 13" reels in accordance with EIA Standard 481. This packaging system is compatible with all tape-fed automatic pick and place systems. See Table 2 for details on reeling quantities for commercial chips.




Table 5 – Carrier Tape Configuration, Embossed Plastic & Punched Paper (mm)

| | Tape | Embosse | ed Plastic | Punched Paper | | |
|----------------------|------|---------|--------------------|---------------|----------|--|
| EIA Case Size | Size | 7" Reel | 13" Reel | 7" Reel | 13" Reel | |
| | (W)* | Pitch | (P ₁)* | Pitch (P₁)* | | |
| 01005 – 0402 | 8 | | | 2 | 2 | |
| 0603 | 8 | | | 2/4 | 2/4 | |
| 0805 | 8 | 4 | 4 | 4 | 4 | |
| 1206 – 1210 | 8 | 4 | 4 | 4 | 4 | |
| 1805 – 1808 | 12 | 4 | 4 | | | |
| ≥ 1812 | 12 | 8 | 8 | | | |
| KPS 1210 | 12 | 8 | 8 | | | |
| KPS 1812 & 2220 | 16 | 12 | 12 | | | |
| Array 0508 & 0612 | 8 | 4 | 4 | | | |

^{*}Refer to Figures 1 & 2 for W and P_1 carrier tape reference locations.

New 2 mm Pitch Reel Options*

| Packaging Ordering Code (C-Spec) | Packaging Type/Options |
|--|------------------------------------|
| C-3190 | Automotive grade 7" reel unmarked |
| C-3191 | Automotive grade 13" reel unmarked |
| C-7081 | Commercial grade 7" reel unmarked |
| C-7082 | Commercial grade 13" reel unmarked |

^{* 2} mm pitch reel only available for 0603 EIA case size. 2 mm pitch reel for 0805 EIA case size under development.

Benefits of Changing from 4 mm to 2 mm Pitching Spacing

- Lower placement costs
- Double the parts on each reel results in fewer reel changes and increased efficiency
- Fewer reels result in lower packaging, shipping and storage costs, reducing waste

^{*}Refer to Tables 6 & 7 for tolerance specifications.



Figure 1 – Embossed (Plastic) Carrier Tape Dimensions




Table 6 – Embossed (Plastic) Carrier Tape Dimensions

Metric will govern

| | Constant Dimensions — Millimeters (Inches) | | | | | | | | | |
|-----------|--|----------------------------------|------------------------------|-----------------------------|------------------------------|---------------------------|----------------------------------|--------------------------------|---------------------------|--|
| Tape Size | D ₀ | D ₁ Minimum Note 1 | E ₁ | P ₀ | P ₂ | R Reference Note 2 | S ₁ Minimum Note 3 | T Maximum | T ₁ Maximum | |
| 8 mm | | 1.0 (0.039) | | | | 25.0 (0.984) | | | | |
| 12 mm | 1.5 +0.10/-0.0 (0.059 +0.004/-0.0) | 1.5 | 1.75 ±0.10 (0.069 ±0.004) | 4.0 ±0.10 (0.157 ±0.004) | 2.0 ±0.05 (0.079 ±0.002) | 30 | 0.600 (0.024) | 0.600 (0.024) | 0.100 (0.004) | |
| 16 mm | | (0.059) | | | | (1.181) | | | | |
| | Variable Dimensions — Millimeters (Inches) | | | | | | | | | |
| Tape Size | Pitch | B ₁ Maximum Note 4 | E ₂ Minimum | F | P ₁ | T ₂ Maximum | W Maximum | A ₀ ,B ₀ | & K ₀ | |
| 8 mm | Single (4 mm) | 4.35 (0.171) | 6.25 (0.246) | 3.5 ±0.05 (0.138 ±0.002) | 4.0 ±0.10 (0.157 ±0.004) | 2.5 (0.098) | 8.3 (0.327) | | | |
| 12 mm | Single (4 mm) & Double (8 mm) | 8.2 (0.323) | 10.25 (0.404) | 5.5 ±0.05 (0.217 ±0.002) | 8.0 ±0.10 (0.315 ±0.004) | 4.6 (0.181) | 12.3 (0.484) | Not | e 5 | |
| 16 mm | Triple (12 mm) | 12.1 (0.476) | 14.25 (0.561) | 7.5 ±0.05 (0.138 ±0.002) | 12.0 ±0.10 (0.157 ±0.004) | 4.6 (0.181) | 16.3 (0.642) | | | |

- 1. The embossment hole location shall be measured from the sprocket hole controlling the location of the embossment. Dimensions of embossment location and hole location shall be applied independent of each other.
- 2. The tape with or without components shall pass around R without damage (see Figure 6).
- 3. If S₄ < 1.0 mm, there may not be enough area for cover tape to be properly applied (see EIA Standard 481 paragraph 4.3 section b).
- 4. B, dimension is a reference dimension for tape feeder clearance only.
- 5. The cavity defined by A_{α} , B_{α} and K_{α} shall surround the component with sufficient clearance that:
 - (a) the component does not protrude above the top surface of the carrier tape.
 - (b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been removed.
 - (c) rotation of the component is limited to 20° maximum for 8 and 12 mm tapes and 10° maximum for 16 mm tapes (see Figure 3).
 - (d) lateral movement of the component is restricted to 0.5 mm maximum for 8 and 12 mm wide tape and to 1.0 mm maximum for 16 mm tape (see Figure 4).
 - (e) for KPS Series product, A_0 and B_0 are measured on a plane 0.3 mm above the bottom of the pocket.
 - (f) see Addendum in EIA Standard 481 for standards relating to more precise taping requirements.



Figure 2 – Punched (Paper) Carrier Tape Dimensions




Table 7 – Punched (Paper) Carrier Tape Dimensions

Metric will govern

| | Constant Dimensions — Millimeters (Inches) | | | | | | | | | | |
|-----------|--|------------------------------|-----------------------------|-----------------------------|----------------------------|-----------------|-----------------------|--|--|--|--|
| Tape Size | D ₀ | E ₁ | P ₀ | P ₂ | T ₁ Maximum | G Minimum | R Reference Note 2 | | | | |
| 8 mm | 1.5 +0.10 -0.0 (0.059 +0.004 -0.0) | 1.75 ±0.10 (0.069 ±0.004) | 4.0 ±0.10 (0.157 ±0.004) | 2.0 ±0.05 (0.079 ±0.002) | 0.10 (0.004) Maximum | 0.75 (0.030) | 25 (0.984) | | | | |
| | Variable Dimensions — Millimeters (Inches) | | | | | | | | | | |
| Tape Size | Pitch | E2 Minimum | F | P ₁ | T Maximum | W Maximum | A_0B_0 | | | | |
| 8 mm | Half (2 mm) | 6.25 | 3.5 ±0.05 | 2.0 ±0.05 (0.079 ±0.002) | 1.1 | 8.3 (0.327) | Note 1 | | | | |
| 8 mm | Single (4 mm) | (0.246) | (0.138 ±0.002) | 4.0 ±0.10 (0.157 ±0.004) | (0.098) | 8.3 (0.327) | Note 1 | | | | |

- 1. The cavity defined by A_n, B_n and T shall surround the component with sufficient clearance that:
 - a) the component does not protrude beyond either surface of the carrier tape.
 - b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been removed.
 - c) rotation of the component is limited to 20° maximum (see Figure 3).
 - d) lateral movement of the component is restricted to 0.5 mm maximum (see Figure 4).
 - e) see Addendum in EIA Standard 481 for standards relating to more precise taping requirements.
- 2. The tape with or without components shall pass around R without damage (see Figure 6).



Packaging Information Performance Notes


- 1. Cover Tape Break Force: 1.0 Kg minimum.
- 2. Cover Tape Peel Strength: The total peel strength of the cover tape from the carrier tape shall be:

| Tape Width | Peel Strength |
|--------------|----------------------------------|
| 8 mm | 0.1 to 1.0 Newton (10 to 100 gf) |
| 12 and 16 mm | 0.1 to 1.3 Newton (10 to 130 gf) |

The direction of the pull shall be opposite the direction of the carrier tape travel. The pull angle of the carrier tape shall be 165 $^{\circ}$ to 180 $^{\circ}$ from the plane of the carrier tape. During peeling, the carrier and/or cover tape shall be pulled at a velocity of 300 \pm 10 mm/minute.

3. Labeling: Bar code labeling (standard or custom) shall be on the side of the reel opposite the sprocket holes. *Refer to EIA Standards 556 and 624.*

Figure 3 – Maximum Component Rotation






Figure 4 - Maximum Lateral Movement




Figure 5 - Bending Radius







Figure 6 – Reel Dimensions



Note: Drive spokes optional; if used, dimensions B and D shall apply.

Table 8 - Reel Dimensions

Metric will govern

| | Constant Dimensions — Millimeters (Inches) | | | | | | | | | | |
|-----------|--|---------------------------------------|--|---|--|--|--|--|--|--|--|
| Tape Size | A | B Minimum | С | D Minimum | | | | | | | |
| 8 mm | 178 ±0.20 | | | | | | | | | | |
| 12 mm | (7.008 ±0.008) | 1.5 (0.059) | 13.0 +0.5/-0.2 (0.521 +0.02/-0.008) | 20.2 (0.795) | | | | | | | |
| 16 mm | 330 ±0.20 (13.000 ±0.008) | (41333) | (0.02) 0.02) | (* ***) | | | | | | | |
| | Variable | Dimensions — Millimeter | rs (Inches) | | | | | | | | |
| Tape Size | N Minimum | W ₁ | W ₂ Maximum | W_3 | | | | | | | |
| 8 mm | | 8.4 +1.5/-0.0 (0.331 +0.059/-0.0) | 14.4 (0.567) | | | | | | | | |
| 12 mm | 50 (1.969) | 12.4 +2.0/-0.0 (0.488 +0.078/-0.0) | 18.4 (0.724) | Shall accommodate tape width without interference | | | | | | | |
| 16 mm | | 16.4 +2.0/-0.0 (0.646 +0.078/-0.0) | 22.4 (0.882) | | | | | | | | |



Figure 7 – Tape Leader & Trailer Dimensions





Figure 8 – Maximum Camber





KEMET Corporation World Headquarters

2835 KEMET Way Simpsonville, SC 29681

Mailing Address: P.O. Box 5928 Greenville, SC 29606

www.kemet.com Tel: 864-963-6300 Fax: 864-963-6521

Corporate Offices Fort Lauderdale, FL Tel: 954-766-2800

North America

Northeast

Wilmington, MA Tel: 978-658-1663

Southeast

Lake Mary, FL Tel: 407-855-8886

Central

Novi, MI

Tel: 248-994-1030

Irving, TX

Tel: 972-915-6041

West

Milpitas, CA Tel: 408-433-9950

Mexico

Guadalajara, Jalisco Tel: 52-33-3123-2141

Europe

Southern Europe Sasso Marconi, Italy Tel: 39-051-939111

Skopje, Macedonia Tel: 389-2-55-14-623

Central Europe Landsberg, Germany Tel: 49-8191-3350800

Kamen, Germany Tel: 49-2307-438110

Northern Europe

Wyboston, United Kingdom Tel: 44-1480-273082

Espoo, Finland Tel: 358-9-5406-5000

Asia

Northeast Asia Hong Kong Tel: 852-2305-1168

Shenzhen, China Tel: 86-755-2518-1306

Beijing, China Tel: 86-10-5877-1075

Shanghai, China Tel: 86-21-6447-0707

Seoul, South Korea Tel: 82-2-6294-0550

Taipei, Taiwan Tel: 886-2-27528585

Southeast Asia

Singapore

Tel: 65-6701-8033

Penang, Malaysia Tel: 60-4-6430200

Bangalore, India Tel: 91-806-53-76817

Note: KEMET reserves the right to modify minor details of internal and external construction at any time in the interest of product improvement. KEMET does not assume any responsibility for infringement that might result from the use of KEMET Capacitors in potential circuit designs. KEMET is a registered trademark of KEMET Electronics Corporation.



Disclaimer

All product specifications, statements, information and data (collectively, the "Information") in this datasheet are subject to change. The customer is responsible for checking and verifying the extent to which the Information contained in this publication is applicable to an order at the time the order is placed.

All Information given herein is believed to be accurate and reliable, but it is presented without guarantee, warranty, or responsibility of any kind, expressed or implied.

Statements of suitability for certain applications are based on KEMET Electronics Corporation's ("KEMET") knowledge of typical operating conditions for such applications, but are not intended to constitute – and KEMET specifically disclaims – any warranty concerning suitability for a specific customer application or use. The Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by KEMET with reference to the use of KEMET's products is given gratis, and KEMET assumes no obligation or liability for the advice given or results obtained.

Although KEMET designs and manufactures its products to the most stringent quality and safety standards, given the current state of the art, isolated component failures may still occur. Accordingly, customer applications which require a high degree of reliability or safety should employ suitable designs or other safeguards (such as installation of protective circuitry or redundancies) in order to ensure that the failure of an electrical component does not result in a risk of personal injury or property damage.

Although all product—related warnings, cautions and notes must be observed, the customer should not assume that all safety measures are indicted or that other measures may not be required.